CODE QE-735 LOT E810

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	76	3800		
	STUMP Lamp-3889			

TOTAL NET WT. 3800 PKG. N–CODE 1201

PROD. SPVR. DATE WHSE. OPER.

5/11/01

35/241

E1210

CG 01 CODE YE-735-D PKG.

→ APR -0-81- [redacted]

EST. WGT. 4021 LBS.

dk/A

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YE-735-D (K)	JHK
	DCG 4-19-78
TYPED BY	

MAKING NOTES

REMARKS

NAME: NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
VAT	241				
DATE	5/8/81				
TIME	6:20 PM	JK			
RELEASED BY	CAK				
PRESS	2	91			
NO. OF CAKES	32	42			

PRESS WITH AGITATION SEE BELOW

WASH TO 3500 OHMS WITH 35-75°F WATER

TEST AFTER 2 HOURS

LOAD ON 5 CARS

STOP AGITATOR AT ABOUT 50"

DO NOT EXTRUDE

SAMPLES BLL

DELIVER TO

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7PM				
CAKES USED	32				
WATER ON	10PM				
HRS. WASHED	8				
OHMS	4000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	5				
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY RELEASED BY [signature]

-DRYING-

12 HRS AT 240°F

LUMP: - OK - WET - SALTS - CONTAMINATE

Cannot account for low yield. No record of any processing losses

ADDITIONAL DRYING HOURS REQUIRED ____ #

SAMPLES

DELIVER TO

NO. CARS PULLED 11 LUMP WGT. 3889

SAMPLED BY RELEASED BY [signature]

-GRINDING-

MIKROATOMIZE

SET ROOF GATE AT 5 INCHES AIR FLOW

MAGNEHELIC READING ON ATOMIZER PANEL BOARD (1.0")

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 [illegible] & 2 PT CANS

DELIVER TO C T L

DATE MIXED

DUP050096053

1210
12
365

3.71 +
0.12 -
3.77 +
0.12 -
3.84 +
0.12 -
3.67 +
0.12 -
4.05 +
0.12 -
3.68 +
0.12 -
3.74 +
0.12 -
3.86 +
0.12 -
3.76 +
0.12 -
3.43 +
0.12 -
2.70 +
0.12 -
38.89 +

DUP050096054