

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE XC-10 LOT A2K98

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

<u>50</u>	<u>113</u>	<u>5650</u>		

STUMP

TOTAL NET WT. 5650 PKG. N-CODE _____

PROD. SPVR. _____ DATE _____ WHSE. OPER. _____

5/1 2 18 1

EST./WT. 5575* LBS.

NON-BLEEDING

PROCESSES

APPROVED BY

YC-010-B (G) FWP 10/07/81

ALTERNATE

TYPED BY JMM

MAKING NOTES

JOB NAME: 01YC010BPG

INSTRUCTIONS

VAT 242
DATE 2-1-82
TIME 2:30 PM
RELEASED BY P.N.I. [Signature]
PRESS 2 92 93
NO. OF CAKES 54 54 54
PRESS WITH AGITATION
WASH TO 500 M MHOS WITH 35-75* WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

= PRESSING =

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
M MHOS
HRS. WASHED
M MHOS
HRS. WASHED
M MHOS
CAKE CONDITION
NO CARS LOADED
EXPLAIN LOSSES

RECORD

1ST	2ND	3RD	4TH	5TH
B38 5 62H 3010				
3-12				

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED B

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

=====

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY *L*

NO DRUMS 18
LUMP WGT 5517

GRINDING

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT '9" FOR
HIGH AIR FLOW

SCREEN	RPM
MAX. TEMP.	F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV.
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

90
41
130
0

331
12
332
12
344
12
350
12
362
12
355
12
331
12
243
12
552

	90
124	1
41	0
304	
14	
301	
14	
200	
14	
224	
14	
252	
361	5

3615
311
12
326
12
335
12
331
12
331
12
340
12
5517