MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE YT865 LOT 34219

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	14	2049	37	

STUMP

TOTAL NET WT. 2049 PKG. N--CODE

PROD. SPVR. DATE 2/10/ WHSE. OPER. 222

DUP050293141

N33056.01

3
105

CG 46 CODE YT-868-D PKG. ____

→ FEB-4 34219

EST. WGT. ~~2253~~ ~~2244~~ LBS.
2253

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YT-868-D (A)	EWK 9/30/76
	EAS 5/26/78
	DCG 5/30/78
TYPED BY	

MAKING NOTES

REMARKS

119# Dust Drum

NAME: DALAMAR® YELLOW

BLEEDING

-PRESSING-

INSTRUCTIONS

AT				105
ATE			(JW)	2-5-80
IME				2:45
ELEASED BY				K.A.
RESS	32	33	35	36
O. OF CAKES	60	60	60	60

RESS without AGITATION
ASH TO 4000 OHMS with 35-75°F water
EST AFTER 6 HOURS
OAD on 10 cars

DO NOT LOAD BOTTOM 2 ROWS OF CARS

AMPLES [redacted] gal (2 gallon
DELIVER TO

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	[illegible]				
CAKES USED	60				
WATER ON	9PM				
HRS. WASHED	6 HRS				
OHMS	4000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	9				

EXPLAIN LOSSES

SAMPLED BY 169 RELEASED BY JD

-DRYING-

RY - 30 HOURS AT - 180 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

No Record of any Processing Loss

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 14

AMPLES 1 qt
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 2089
RELEASED BY BLL

-GRINDING-

MILL 4 or 10 HSP1/8"RP CREEN 3500 RPM
MAX. TEMP. °F

CO2 USAGE: 10-11-10 %
OXYGEN

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES 119# Dust Drum

SAMPLE A~~FTER~~ / WITHOUT MIXING
SAMPLES /ENV + 1 PT can + 1 qt
DELIVER TO C T L

DATE MIXED
SAMPLED BY 227 RELEASED BY

DUP050293142

N33056.02



DUP050293143

N33056.03