CODE Ky. 795 LOT 35558

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2330	1	T. 113		
2410	1	T. 69		
	Comp			
	~~STUMP~~	4666		

TOTAL NET WT. 4740 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
SM	5,7,80	

95/262

CG 03 CODE KY-795-D PKG. APR 29 35558

→

EST. WGT. ~~1178~~ 938 LBS.

7:AM

OK

AP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-795-D (1)	EWK 10/6/76
Alternate	DCG 10/7/76
TYPED BY	
NE 3/3/77	

emw031579 MAKING NOTES FWP 03-15-79

REMARKS

Total Wgt: ~~4878#~~ 4638

NAME: "KROLOR" YELLOW-MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS

AT			262		
ATE			S-1		
IME			130		
ELEASED BY			Sy	(95)	40
RESS	22	23	24	24	25
. OF CAKES	46	46	46	52	48

RESS with AGITATION

SH TO 5000 OHMS

ST AFTER 5 HOURS with 35-75°F water

AD on 5 cars

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	6				
CAKES USED	40				
WATER ON	10				
HRS. WASHED	7				
OHMS	5500				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLES 1-8 oz JAR

DELIVER TO CTL for color

SAMPLED BY RELEASED BY A.K.

-DRYING-

Dry 14 Hrs at 220°F

NOTE: If dried in 12-23, 80-97, or 138-155 sections:
- dry for 14 hrs at 220°F
- record sections:
- fill in additional hrs required if any

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

No Drum 14

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

LUMP WGT. 4666

RELEASED BY

-GRINDING-

ALL 939 HSP 3/32" RP SCREEN 1500 RPM

MAX. TEMP. 210 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env & 1 Pt Can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050456398

N32051.01

3 5 5.5 8 N
.4 1 N
.1 6 N
.0 0 T

3.6 8
.1 2 "
3.5 6
.1 2 "
3.4 7
.1 2 "
3.4 9
.1 2 "
3.6 8
.1 2 "
3.7 1
.1 2 "
3.6 5
.1 2 "
3.5 0
.1 2 "
3.5 6
.1 2 "
3.8 7
.1 2 "
3.5 9
.1 2 "
3.5 4
.1 2 "
3.5 5
.1 2 "
1.4 9
.1 2 "
4 6.6 6 T

DUP050456399

N32051.02