

WHITE - Lt. Grey, Ivory, Green, Buff EMELITE HOUSE PAINT

Ingredient	Formula in lbs.		Yield in Gals.		Unit cost per pound or gal.		Total cost of ingredients	
	Before Change	After Change	Before Change	After Change	Before Change	After Change	Before Change	After Change
Pigment								
White Lead Carbonate	135	135	2.4	2.4	.085	.085	11.48	11.48
" " Sulphate	231	231	4.4	4.4	.075	.075	17.33	17.33
Zinc Oxide	201	201	4.3	4.3	.075	.075	15.08	15.08
Titanium Pigment	241	241	6.2	6.2	.055	.055	13.26	13.26
Asbestine	192	192	8.1	8.1	.0125	.0125	2.40	2.40
Vehicle								
White Refined	199	80	25.7	10.3	.165	.165	32.84	13.20
Raw Linseed oil	180	80	23.2	10.3	.151	.151	27.18	12.08
Bodied " " (Zl-22 Body)	43	164	5.3	20.5	.195	.195	8.38	31.98
Driers	6.3	6.3	1.04	.79	1.00	1.00	1.04	.79
Mineral Spirit	56	143	8.9	22.0	.105	.105	.93	2.31
Calculated Yield			89.54	89.29				
Manufacturing Loss 2 1/2%			2.22	2.21				
Actual Yield			87.32	87.08				
Material Cost of White per Gal.							1.48	1.38
Material Cost of Tints per Gal.							1.54	1.44

Ever Leaf Paint & Varnish Corporation
Long Island City, New York

REPRODUCED AT THE NATIONAL ARCHIVES

OPA 26015

N 4408