

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Ky 787 LOT E1494

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

50 71 3.550**STUMP** Lump 3,449TOTAL NET WT. 3,550 PKG. N-CODE 1000

PROD. SPVR.

DATE

WHSE. OPER.

JIT 5/24/81

2/10
CG 03 CODE KY-787-D PKG.
→ MAY -081-31494
EST. WGT. XXXXX 932 LBS.
33324
Total Wgt. 34900

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (K)	FWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NE 2/12/77	
MAKING NOTES	

REMARKS

ME: KROLOR - YELLOW MEDIUM NON-BLEEDING

INSTRUCTIONS					-PRESSING-	RECORD				
AT	240				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE	5:40 PM				STARTED	8:30				
ME	4:30 PM				CAKES USED	35				
RELEASED BY	ES				WATER ON	1:30				
RESS	22	23	24	24	HRS. WASHED	7				
NO. OF CAKES	46	46	46	52	OHMS	3000				
RESS with	AGITATION					HRS. WASHED				
ASH TO 2000	OHMS with 35-75°F water					OHMS				
EST AFTER	2	HOURS			HRS. WASHED					
OAD on 6 cars						OHMS				
					CAKE CONDITION					
					NO. CARS LOADED	6				
					EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
ELIVER TO c1 for color

SAMPLED BY RELEASED BY B/L

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F.

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES NO. OF CARS PULLED
ELIVER TO INV & 1 P. LUMP WGT. 3449
CT L RELEASED BY

-GRINDING-

ALL 049 1" P 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES INV & 1 P.
ELIVER TO CT L

DATE MIXED
SAMPLED BY RELEASED BY

4194
4100
158

0.00 *

2.64 +
0.12 -
2.49 +
0.12 -
2.75 +
0.12 -
2.65 +
0.12 -
2.60 +
0.12 -
2.69 +
0.12 -
2.76 +
0.12 -
2.77 +
0.12 -
2.70 +
0.12 -
2.81 +
0.12 -
2.54 +
0.12 -
2.52 +
0.12 -
2.53 +
0.12 -
1.72 +
0.12 -
34.49 *