

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 10/2 758 LOT E1004

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>71</u>	<u>3500</u>		

STUMP

TOTAL NET WT. 3500 PKG. N-CODE 1000

PROD. SPVR. 10/2 DATE 5-2-81 WHSE. OPER.

EST. WGT. 960 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-788-D (J)

APPROVED BY
ENK 9/22/76

DCG 9/27/76

TYPED BY

NE 2/17/77

MAKING NOTES

REMARKS

Total Wgt. 35664 Req()

NAME: "KROLOR" YELLOW - LIGHT

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	244					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5/5/51					STARTED	4 PM				
TIME	11:30 A					CAKES USED	54				
RELEASED BY	33					WATER ON	1 AM				
PRESS	22	23	24			HRS. WASHED					
NO. OF CAKES	46	46	46			OHMS	28.0				
PRESS With	AGITATION					HRS. WASHED					
WASH TO 2000	OHMS with 35-75°F water					OHMS					
TEST AFTER 2	HOURS					HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	7				
						EXPLAIN LOSSES					

SAMPLES 1- 8oz JAR
DELIVER TO Ctl. for Color

SAMPLED BY 43 RELEASED BY

-DRYING-

Dry 12 hrs at 220 °F
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATE

The record of any proceedings
Torres had, released.

ADDITIONAL DRYING HOURS REQUIRED

**SAMPLES
DELIVER TO**

NO. CARS PULLED
SAMPLED BY

No Drums *JS*
LUMP WGT. *3522*
RELEASED BY *RH*

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN	RPM
MAX. TEMP.	° F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

DATE MIXED

SAMPLES 1 Env. & 1 Pt can

SAMPLED BY

DELIVER TO C T L

RELEASED BY

1404
41
158

2.71	+
0.12	✓
2.42	+
0.12	✓
2.60	+
0.12	✓
2.69	+
0.12	✓
2.64	+
0.12	✓
2.56	+
0.12	✓
2.43	+
0.12	✓
2.45	+
0.12	✓
2.78	+
0.12	✓
2.42	+
0.12	✓
2.66	+
0.12	✓
2.56	+
0.12	✓
2.70	+
0.12	✓
2.18	+
0.12	✓
1.22	+
0.12	✓
35.22	*