MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky 908 LOT 33932

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2210	1		T-110	
2202	1		T-298	
1924	1		T-173	

STUMP

TOTAL NET WT. 6336 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

WK 1/27/80

N 2641

95
262

CG 03 CODE KY-908-D PKG. ____

JAN 2 B 33932

EST. WGT. 1603 LBS.

OK
AP

33932

TOTAL WGT 6203#

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-908-D (F)	EWK 12/12/77
Alternate	DCG 12/14/77
TYPED BY	
rj 2/6/78	

MAKING NOTES

REMARKS

AME: KROLOR® YELLOW - LIGHT

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
AT	262					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE	1-24-80					STARTED	6 Hrs				
IME	500 A					CAKES USED	72				
ELEASED BY	[illegible]					WATER ON	730AM				
RESS	96	95				HRS. WASHED	6				
O. OF CAKES	72	72				OHMS	2000				
RESS with		AGITATION				HRS. WASHED					
ASH TO 2000		OHMS				OHMS					
EST AFTER 3		HOURS with 135-145°F water				HRS. WASHED					
on 10 cars						OHMS					
						CAKE CONDITION					
TDS						NO. CARS LOADED	9				
						EXPLAIN LOSSES					

AMPLES 8oz Jar

ELIVER TO CIL for color

SAMPLED BY RELEASED BY T.D.S

-DRYING-

RY 24 HOURS AT 180 °F

LUMP: - OK - WET - SALTS - CONTAMINATE

Color Appears Dry

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 20

AMPLES

NO. CARS PULLED

LUMP WGT. 6405

ELIVER TO

SAMPLED BY RELEASED BY BLL

-GRINDING-

3/32

ILL 939 HSP ~~1/8~~" RP SCREEN 3500 RPM

SCREEN RPM

AX. TEMP. 170°F

MAX. TEMP. °F

EXPLAIN LOSSES

AMPLE / WITHOUT MIXING

DATE MIXED

AMPLES 1 ENV & TPTCAN

ELIVER TO CIL

SAMPLED BY RELEASED BY

DUP050094229

N 26410.01

0.00 *

33932
41
294

0.00 *

3.29 +
0.14 -
3.29 +
0.14 -
3.28 +
0.14 -
3.41 +
0.14 -
3.24 +
0.14 -
3.34 +
0.14 -
3.38 +
0.14 -
3.31 +
0.14 -
3.41 +
0.14 -
3.32 +
0.14 -
3.40 +
0.14 -
3.31 +
0.14 -
3.31 +
0.14 -
3.43 +
0.14 -
3.39 +
0.14 -
3.38 +
0.14 -
3.35 +
0.14 -
3.42 +
0.14 -
3.49 +
0.14 -
3.10 +
0.14 -
64.05 *

DUP050094230