

INDUSTRIAL HYGIENE RESULTS

DATE: March 25, 1983.

PROJECT: Identify samples of insulation picked up at several locations in the Steam Plant.

DATE OF SAMPLES: 3-9-83, 3-17-83

SUMMARY:

<u>DATE</u>	<u>SAMPLE FROM</u>	<u>IDENTITY</u>
3-9-83	T-49, condensate tank	Appears to contain some asbestos.
3-9-83	Scrap insulation on 1st level above ground, N-W corner #1 boiler	No asbestos, all glass fibers
3-17-83	White residue, 4th level #1 boiler	Appears to be sodium and iron carbonates, no asbestos

RECOMMENDATIONS: Follow asbestos procedure while removing insulation from T-49 condensate tank.

Share this information with Energy Systems and Maintenance personnel.

METHOD OF ANALYSIS: Chemical microscopy

DATA AND REPORT BY: H. G. Kuntz/K. E. Williams

ANALYSIS BY: V. H. McCool

COPY TO: ✓ M. W. Bosserman, T. Bossick, R. E. Cashdollar,
J. E. McDermott, J. B. Mickey, K. R. Mosley,
A. G. Olds, F. M. Plechaty.


K.E. Williams