CG 18 CODE GP-501-D PKG. ____

→ Aug 8 00219

EST. WGT. 0 [redacted] LBS.

FIRE PORTION

SPLIT-OFF ±150# From GP501D Lot 32693
FIRED IN DRYER To be DISCARDED.
TOTAL DISCARDED 106#

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
GP-501-D (P)	EWK 03-17-75
	DCG 03-17-75
TYPED BY	
emw062979	

MAKING NOTES

REMARKS

NAME: RAMAPO® GREEN B — NON-BLEEDING

-PRESSING-

INSTRUCTIONS					RECORD					
VAT					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE					STARTED					
TIME					CAKES USED					
RELEASED BY					WATER ON					
PRESS	12	20	21	26	HRS. WASHED					
NO. OF CAKES	3 x 36	2 x 42	2 x 42	3 x 40	OHMS					
PRESS with AGITATION					HRS. WASHED					
WASH TO 4000 OHMS with 35-75°F water					OHMS					
TEST AFTER 3 HOURS					HRS. WASHED					
LOAD on 8 cars					OHMS					
					CAKE CONDITION	9				
					NO. CARS LOADED					
					EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY RELEASED BY

-DRYING-

Dry 12 hrs at 180°F
Dry 12 hrs at 140°F

Std & Abrev Dry P & S
Sides 180 DN
Cool - 100
Use 41 Gal L/P

LUMP: - OK - WET - SALTS - CONTAMINATE
Dryer sections used:

ADDITIONAL DRYING HOURS REQUIRED

PUNCHED & CHECKED
SEP 2 3 1980

NO. DRUMS

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT.
SAMPLED BY RELEASED BY

-GRINDING-

MILL 7 or 8 LSP 3/32" RP SCREEN 1785 RPM
MAX. TEMP. °F
Use 41 Gal L/P

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 Env & 2 Pt Cans
DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY