

LOT
A2H61
WT. 2737 LBS.

96
901

15

ALTERNATE
TYPED BY JMH

MAKING NOTES INSTRUCT MAKING AREA TO
ADD 100 N-588-A HALFWAY THRU PRESSING
***IF POSSIBLE AIR BLOW 15 MIN BEFORE
WASH***
JOB NAME 32RT761DPH

INSTRUCTIONS		PRESSING		RECORD					
				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	11-5-82			STARTED	12:44				
TIME	9:45 AM			CAKES USED	20				
RELEASED BY	ES			WATER ON	5A				
PRESS	25	56	H1	HRS. WASHED	17 1/2				
NO. OF CAKES	80	36	NA	OHMS	325				
PRESS WITHOUT AGITATION				HRS. WASHED					
WASH TO 3000 OHMS- WITH 35-75 F WATER				OHMS					
TEST AFTER 4 HOURS				HRS. WASHED					
LOAD ON 10 CARS				OHMS					
PRESS IMMEDIATELY CODE				CAKE CONDITION	13				
CLEAN MAGNETIC SEPARATOR AFTER PRESSING				NO CARS LOADED					
CLEANED BY:				WASH WATER TEMP					
TIME CLEANED				EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 20 HOURS AT 220 DEG F
COOL TO 150 DEG F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 2677

= GRINDING =

MILL #2 ~~1/8~~ 1/8" RP SCREEN ~~1800~~ RPM
MAX. TEMP 170 DEG F 1800

SCREEN
MAX. TEMP. RPM
F

INERT MILL WITH CO₂ WHEN GRINDING PER O.P. # 0.5 0.43

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLE 1 ENV & 2 PINTS
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

11/11/82
213

15 DRS

61
51
294

RT 061

0.00

1.90	+
0.12	-
1.84	+
0.12	-
1.92	+
0.12	-
1.93	+
0.12	-
1.84	+
0.12	-
1.99	+
0.12	-
1.87	+
0.12	-
2.01	+
0.12	-
1.91	+
0.12	-
1.97	+
0.12	-
1.89	+
0.12	-
1.94	+
0.12	-
2.00	+
0.12	-
1.91	+
0.12	-
1.60	+
0.12	-
26.77	*