

Johns-Manville FINISHED PRODUCT SPECIFICATION	PRODUCT:	DIVISION	II
	SUPEREX FURNACE BLOCKS (PLAIN)	SPEC NO.	432-4
	SUPEREX FURNACE BLOCKS (SILICATED)	PAGE NO.	4.

V. QUALITY REQUIREMENTS:

Note: Values determined on Superex Furnace Block (Plain) except as noted.

A. Density (lbs/cu ft)

Desired Maximum	-	24#
Maximum	-	27#

B. Modulus of Rupture (psi)

Minimum	-	60
---------	---	----

C. Abrasion Loss (percent)

1. 10 min.	-	40 maximum
2. 20 min.	-	70 maximum

D. Hardness (m.m. by Plastometer) Plain

0.75 max. (avg. 5 samples)	<u>As Received</u>
	<u>Silicated</u>
	0.4 max. (avg. 5 samples)
	0.5 max. (individual)

E. Change after Soaking Heat

1. Hardness (4 hrs. at 1900°F)	-	0.9 m.m. maximum
2. Loss in Weight (24 hrs. at 1900°F)	-	10% maximum

F. Linear Shrinkage (percent) (Tested on Unsilicated Block)

1. After 24 hrs. at 1900°F	1.5% average
	2.0% maximum

G. Magnesia Content - 6% optimum

VI. PACKAGING:

Cases or cartons. Cases when sawdust is used.

Note: Trapezoidal Blocks for American Brake Shoe Co. (4" thick x 6" x 5-1/8") shall be packaged 12 pcs. per 11-5/8" x 12-1/2" x 36-1/4" carton.

For additional packaging information consult Packaging Specification Magnesia and Superex 432-5.

DEFENDANT'S
EXHIBIT

QT-247

PLAINTIFF'S
EXHIBIT
K-1675

RETURN TO

J.M. RESEARCH
FILE ROOM

X- INDICATES REASON: Reduction in shrinkage maximum

AUTHORITY FOR CHANGE Interim Agreement to Product Proposal 011-1027

SUPERSEDES: Page 4 same specification issued 5/11/59

DIR. Q.C.	MGR. Q.C.	SUPR. Q.C.	PROD. SUPT.	PLNT. FN.	RES. LAB.	C.E. Ernst	E.F. Briggs	A. Pocius	DATE ISSUED	2/2/61
--------------	--------------	---------------	----------------	--------------	--------------	---------------	----------------	--------------	----------------	--------