

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-788-D LOT 34926

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>70</u>	<u>3500</u>		

STUMP

TOTAL NET WT. 3500 PKG. N-CODE 1130PROD. SPVR. [Signature] DATE 3/19/80 WHSE. OPER.

N 27522

23
243
CG 03 CODE KY-788-D PKG.

MAR 16 34926

EST. WGT. 960 860 LBS.

OK
KP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES KY-788-D (J)	APPROVED BY EWK 9/22/76
	DCG 9/27/76
TYPED BY NE 2/17/77	

MAKING NOTES

REMARKS

Total Wgt. 3560# Req()

NAME: "KROLOR" YELLOW - LIGHT

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT		243			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		3-16-80			STARTED	2 PM				
TIME		150 PM			CAKES USED	46				
RELEASED BY		MAA			WATER ON	7:30				
PRESS	22	23	24		HRS. WASHED	1.2				
NO. OF CAKES	46	46	46		OHMS	2500				
PRESS With		AGITATION			HRS. WASHED					
WASH TO 2000		OHMS with 35-75°F water			OHMS					
TEST AFTER 2		HOURS			HRS. WASHED					
LOAD on 6 CARS					OHMS					
					CAKE CONDITION	7				
					NO. CARS LOADED					
					EXPLAIN LOSSES					

SAMPLES 1- 80% JAR
DELIVER TO CIL for Color

SAMPLED BY 169 RELEASED BY

-DRYING-

Dry 12 hrs at 220 °F L.V. H.V.
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

No Drums 15
LUMP WGT. 34926
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. & 1 Pt. can
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

3 4 9.2 6 #

.4 1 #

3.5 4 #

.0 0 T

2.6 5

.1 4 -

2.4 7

.1 4 -

2.6 0

.1 4 -

2.6 1

.1 4 -

2.6 1

.1 4 -

2.5 5

.1 4 -

2.6 0

.1 4 -

2.6 7

.1 4 -

2.5 4

.1 4 -

2.4 7

.1 4 -

2.6 1

.1 4 -

2.5 6

.1 4 -

2.6 6

.1 4 -

2.7 0

.1 4 -

.7 2

.1 4 -

3 4.9 2 T