

FORMULAE OF SPECIFIED PAINTS AND VARNISHES

Produced by Three Manufacturers in Chicago, January 1941 - June 1942

MANUFACTURER 'C'Interior Gloss (Enamel)

<u>Percentage Formula</u>		<u>Percentage Formula</u>	
<u>November 1940 to November 1941</u>		<u>December 1941 to June 1942</u>	
	<u>Percent</u>		<u>Percent</u>
<u>Pigment</u>	50.5	<u>Pigment</u>	55.3
Lithopone	79.8	Titanium Dioxide	9.11
Titanium Dioxide	<u>20.2</u>	Lithopone	<u>90.89</u>
	100.0		100.00
<u>Vehicle</u>	49.5	<u>Vehicle</u>	44.7
Varnish and Oils	70.8	Varnish and Oils	71
Thinner and Drier	<u>29.2</u>	Thinner and Drier	<u>29</u>
	100.0		100
	<u>100.0</u>		<u>100.0</u>

Red Lead PaintPercentage FormulaDecember 1940 to June 1942

	<u>Percent</u>
<u>Pigment</u>	69.1
Red Lead	38.4
Silica	30.8
Asbestine	<u>30.8</u>
	100.0
<u>Vehicle</u>	30.9
Boiled Oil	66.9
Raw Linseed Oil	26.7
Drier	<u>6.4</u>
	100.0
	<u>100.0</u>