

③ 45

VISCOSITY WORK SHEET

Item 2107 P.T.No. Date 11/7/55
 Worker Agnes Stanley Polymer Lucite Solvent EDC
 For Shard Charge 1290 Temperature 25°C
 Viscometer No. C Efflux Time 204.0 Weight: Gross 3.6130
 Viscometer No. M Efflux Time 183.2 Tare 3.4880
 Viscometer No. L Efflux Time 180.4 Net 0.1250
 S 167.5 167.3 167.4 167.4
 19 277.0 277.4 276.8 277.1
 Sample Flask No. Solution Efflux Times Rel. Inh. visc.
 Visc. or M.W.

4893-33	5	C	246.4; 246.3; 246.2	1.208	84,500
34	TP	M	230.1; 230.2; 230.3	1.258	111,500
35	H-2	L	249.7; 249.8; 249.7	1.382	187,000
36	998	S	196.5; 196.5	1.173	65,000
37	103	19	350.0; 349.7; 349.9	1.262	112,500
38	M1	C	255.3; 255.7; 255.4	1.252	108,000
39	4-A	M	237.6; 237.4; 237.0	1.295	132,000
40	4-B	L	237.4; 237.3; 237.6	1.316	145,000
41	4-C	S	202.6; 202.8; 202.6	1.211	95,000
42	104	19	359.6; 359.4; 359.5	1.296	133,000
43	4-D	C	259.1; 259.1	1.271	118,000
44	23	M	237.9; 237.8; 237.8	1.298	134,500
45	C	19	388.4; 388.4	1.403	200,000
46	4-E	L	233.6; 233.7; 233.6	1.294	132,000
47	J-31	S	253.9; 254.1; 254.0	1.518	275,000
48	4-F	L	214.0; 214.2; 214.1	1.188	73,000

PC-1

rel
may
11-1-55

N38842