



INTERNAL CORRESPONDENCE

CHEMICALS AND PLASTICS

P. O. BOX 471, TEXAS CITY, TEXAS 77591

TO (NAME) Mr. A. E. Gabany
COMPANY
LOCATION TECH CENTER

DATE March 12, 1976

MAR 17 1976

CC: Mr. R. A. Bleidt - 511
Dr. J. J. Brezinski - 511
Mr. G. F. Tacquard
Mr. R. N. Wheeler - 514

SUBJECT

R N WHEELER, JR.

Dear Al:

Samples have been forwarded to you at the request of John Brezinski for your evaluation of the head space technique recently proposed by EPA. These samples represent the various types of vinyl resins produced at Texas City. Residual VCM analysis of each sample is as follows:

<u>Resin Type</u>	<u>Process</u>	<u>Residual VCM, ppm</u>
QYNL	Non-Solvent	5.1
VYNW	Non-Solvent	3.6
VYHH	Solvent	0.2
VSKK-10	Suspension	237
QSQH-7	Suspension	20.2
QSAN-7	Suspension	40.2
QSAN-7	Suspension	6.6

All samples have been tightly sealed in several layers of polyethylene and sent to you via air mail. Additionally, twenty-five sample vials with caps and septums have been included for your use.

Please let me know if I can assist your efforts in any way or if you have specific questions regarding these selected samples.

Very truly yours,

R. M. Arnold

/kw

UCC
056576

DISTRIBUTION

Texas City

Dr. J. C. Chaty/Dr. D. R. Montgomery
Mr. M. E. Eisenhower
Mr. R. L. Frantz/Mr. F. L. Johnson
Mr. J. L. Mockersmith/Mr. W. C. Roeh
Mr. R. W. Sesler

New York

Mr. G. T. Scott
Mr. G. C. Shipston
Dr. A. B. Steele

South Charleston

— Mr. R. N. Wheeler

Bound Brook

Mr. E. Bell
Mr. R. G. Davis