MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KO.909 LOT 33802

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
2600	1	T251		
	STUMP			

TOTAL NET WT. 2600 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

DATE 1/15/80

N28633

24/245 #2 CLEAN

CG 04 CODE KO-909-D PKG. ____

→ JAN 14 33802

EST. WGT. ~~1674~~ 812 LBS.

OK KP

2612

TOTAL WGT. ~~5274~~ (Req ____)

PROCESSING INSTRUCTIONS - BATCH UNIT

	PROCESSES	APPROVED BY
	KO-909-D (C)	EWK 1-27-78
		DCG 1-30-78
	TYPED BY	
	NSA 3-13-78	

MAKING NOTES

REMARKS

NAME: KROLOR® ORANGE Y — NON-BLEEDING

-PRESSING-

INSTRUCTIONS					RECORD						
AT	245				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE	1-15-80 SL.				STARTED	8 30				
IME	5:45AM				CAKES USED					
ELEASED BY					WATER ON	12:30PM				
RESS	2	22	23	24	HRS. WASHED	5				
O. OF CAKES	46	46	46	~~52~~ 26	OHMS	2500				
RESS with		AGITATION			HRS. WASHED					
ASH TO 2000		OHMS with 135-145° water			OHMS					
EST AFTER		HOURS			HRS. WASHED					
OAD on ~~6~~ 3 cars					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	4				
					EXPLAIN LOSSES					
AMPLES 1-8 oz					SAMPLED BY	197	RELEASED BY			
ELIVER TO CTL for color										

-DRYING-

22

RY ~~24~~ HOURS AT 180°F —

	LUMP: - OK - WET - SALTS - CONTAMINATED
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS : 10
NO. CARS PULLED	LUMP WGT. 2615
SAMPLED BY	RELEASED BY BLL
AMPLES	
ELIVER TO	

-GRINDING-

3/32

ILL 938 HSP ~~1/8~~" RP SCREEN 3500 RPM

AX. TEMP. 170°F

SCREEN	RPM
MAX. TEMP.	°F
EXPLAIN LOSSES	
DATE MIXED	
SAMPLED BY	RELEASED BY

AMPLE / WITHOUT MIXING

AMPLES 1 ENV & 1 PT CAN

ELIVER TO CTL

DUP050095376

33802
41
10

27
1
27
1
26
1
29
1
29
1
29
1
29
1
30
1
18
1
2 6

DUP050095377