



Test Report

TEST ITEMS

Test for *in vitro* cytotoxicity (MTT cytotoxicity test)

TEST ARTICLE

Non-absorbable Surgical Suture (model: PTFE)
<Specification: Z21302-60 (USP2-0/EP2.5)>

IDENTIFICATION №

150642

MANUFACTURER

Foosin Medical Supplies Inc., Ltd.

SPONSOR

TÜV SÜD Certification and Testing (China) Co., Ltd.
<Address: M Building, No.7 Wangjing Zhonghuan Nanlu, Chaoyang District, Beijing 100102,
P.R.China>

NOTICE

1. It will be invalid for the report without a connective seal.
2. It will be invalid for the report without the signature of study director.
3. It will be invalid for the manual revision of the report.
4. It can't be copied partly on the report without agreement, nor can be as the recorder of the order receiving and advertisement registration.
5. Please raise the objection to the Center within 15 days after the receipt of the report, otherwise it will be considered to accept the testing result.
6. It is only responsible for the samples received.

**SHANGHAI BIOMATERIALS RESEARCH & TEST CENTER**

Add: 201, Building 2, № 427 Jumen Road, Shanghai, China

Zip Code: 200023

TEL: 0086-21-63034903

FAX: 0086-21-63034903

Web site: www.sbrtc.com

E-mail: [REDACTED]@163.com

TABLE OF CONTENTS

SUMMARY.....	4
INTRODUCTION.....	5
MATERIALS.....	5~6
METHODS.....	6
DEVIATIONS	7
RESULTS.....	7
CONCLUSION.....	7
RECORD STORAGE.....	7
PHOTOGRAPH OF THE TEST ARTICLE.....	8

SHANGHAI BIOMATERIALS RESEARCH & TEST CENTER

Add: 201, Building 2, № 427 Jumen Road, Shanghai, China

Zip Code: 200023

TEL: 0086-21-63034903

FAX: 00 [REDACTED] 3

Web site: www.sbrtc.com

E-mail: [REDACTED]@163.com

SUMMARY

An in vitro cytotoxicity study was conducted to assess the potential for cytotoxicity of the test article, Non-absorbable Surgical Suture (model: PTFE), based on the International Organization for Standardization ISO 10993-5:2009: Biological evaluation of medical devices - Part 5: Tests for in vitro cytotoxicity; ISO 10993-12:2012: Biological evaluation of medical devices - Part 12: Sample preparation and reference materials.


Four concentrations (100%, 75%, 50%, and 25%) of the test article extracts, the blank, 100% of the negative control and the positive control were prepared using Minimum Essential Medium (MEM) supplemented with 10% fetal bovine serum and 1% L-glutamine. The semi-confluent monolayers of L-929 mouse fibroblast cells were incubated with the test extract, the blank and two controls in a 96-well microplate respectively at 37°C under the condition of 5% CO₂. After 24h, the MTT colorimetric assay was employed and the plate was read on a microplate reader at 570nm (reference wavelength 650 nm). Then the viability of cells was calculated depending on the optical density from the test article extracts and the blank. If the viability of the test sample was reduced to <70% of the blank, it had a cytotoxic potential.

Under the condition of this study, the viability of 100% extract of the test article was 81 %. It can be considered that the test article extracts had not a cytotoxic potential.


Study and Supervisory

Personnel: XU Yuan
HUANG Zhewei

Study Director:



SUN Jiao, Ph.D.



Date Completed

SHANGHAI BIOMATERIALS RESEARCH & TEST CENTER

Add: 201, Building 2, № 427 Jumen Road, Shanghai, China

Zip Code: 200023

TEL: 0086-21-63034903

FAX: 0086-21-63011643

Web site: www.sbrtc.com

E-mail: biomatercenter@163.com

INTRODUCTION

The study was performed in order to determine whether leachables extracted from the test article would cause cytotoxicity. This test was conducted based on the requirements of ISO 10993-5:2009: Biological evaluation of medical devices - Part 5: Tests for *in vitro* cytotoxicity. The test article was received on Jun. 16, 2015. The cells were first exposed to the extract on Oct. 13, 2015, and the final observations were concluded on Oct. 14, 2015.

This study, initiated by protocol signature on Aug. 11, 2015, was completed in the Lab of Shanghai Biomaterials Research & Test Center (SBRTC) and was conducted in accordance with the provisions of the ISO/IEC 17025-2005.

MATERIALS

The test article provided by the sponsor was identified and handled as follows:

Test Article:	Non-absorbable Surgical Suture (model: PTFE) <Specification: Z21302-60 (USP2-0/EP2.5)>
Identification No:	150642
Sterilization Status:	Sterilized
Storage Temperature:	-25~+55°C (declaration from the sponsor)
Extraction Vehicle:	gibco's Minimum Essential Medium (Lot1652143) supplemented with 10% fetal bovine serum (Lot1399413) and 1% L-glutamine (F20150127)
Test Extract Preparation:	Based on the ISO ratio of 6cm ² /ml [Surface area of the test sample to volume of extraction vehicle], 85.5cm ² of the test samples were covered 14.2ml of extraction vehicle under aseptic condition for preparing the test extract at 37°C for 24 hours. The extract was used immediately after extraction.
Blank Preparation:	The extraction vehicle not containing the test sample, retained in a vessel identical to that which holds the test article and subjected to conditions identical to those to which the test sample is subjected during its extraction.
Negative Control Preparation :	High-density polyethylene film (140923), which was current SBRTC negative control (having been demonstrated to be noncytotoxicity) coming from Hatano Research Institute Food and Drug Safety Center, The ratio of 3cm ² : 1ml [surface area of the test sample to volume of extraction vehicle] was used and extracted at 37°C for 24 hours.

SHANGHAI BIOMATERIALS RESEARCH & TEST CENTER

Add: 201, Building 2, № 427 Jumen Road, Shanghai, China

Zip Code: 200023

TEL: 0086-21-63034903

FAX: 0086-21-63034903

Web site: www.sbrtc.com

E-mail: [REDACTED]@163.com

Positive Control Preparation:	Polyurethane film containing 0.1% zinc diethyldithiocarbamate (ZDEC) (140924) which was current SBRTC positive control (having been demonstrated to be severe cytotoxicity) coming from Hatano Research Institute Food and Drug Safety Center. The ratio of 6cm ² : 1ml [surface area of the test sample to volume of extraction vehicle] was used and extracted at 37°C for 24 hours.
Condition of Extracts:	All the extracts of the test and controls were clear and without any special treatments.

METHODS

Test System Management:

Mouse fibroblast cells (L 929, the cell bank of Shanghai Institutes for Biological Sciences, China), were cultured in MEM supplemented with 10% fetal bovine serum and 1% L-glutamine at 37°C in a gaseous environment of 5% carbon dioxide (CO₂). A 96-well microplate method was employed for the MTT colorimetric assay. Each well was seeded 100μl suspension of 1×10⁴ cells, and incubated at 37°C in 5% CO₂ atmosphere for 24h prior to use.

Experimental Procedure:

After incubation, the growth medium was replaced with 100μl four concentrations (100%, 75%, 50% and 25%) of the test extract, 100% of the negative control and the positive control, the blank (row 2 and 11) respectively. Six replicates were prepared for each group. The 96-well plate were incubated at 37°C in 5% CO₂ for 24h.

After 24 h treatment, the culture medium was removed carefully from the plates. 50μl of the MTT (1mg/mL) solution was then added to each test well and the plates were further incubated for 2 h at 37°C in a 5% CO₂ atmosphere. Then the MTT solution was removed and 100μl isopropanol per well was added and shake for 10min by gently. The plate was read on a microplate reader at 570 nm (reference wavelength 650 nm). The viability of the cells was calculated according to the formula below:

$$\text{Viab. \%} = \frac{100 \times OD_{570e}}{OD_{570b}}$$

Where

OD_{570e} is the mean value of the measured optical density of the extracts of the test sample;

OD_{570b} is the mean value of the measured optical density of the blanks;

A test meets acceptance criteria if the left and the right mean of the blanks do not differ by more than 15% from the mean of all blanks. If the viability of the test sample was reduced to <70% of the blank, it had a cytotoxic potential. The 50% extract of the test sample should have at least the same or a higher viability than the 100% extract; otherwise the test should be repeated.

DEVIATIONS

There were no deviations from the ISO 10993-5:2009 and SBRTC-PROTOCOL-1-259.

RESULTS

The mean values of optical density of each group were shown as blow:

Group	The optical density (570nm—650 nm)	Viab. %
100% of the negative control	0.805 ± 0.037	101
100% of the test extract	0.646 ± 0.036	81
75% of the test extract	0.694 ± 0.013	87
50% of the test extract	0.720 ± 0.015	90
25% of the test extract	0.756 ± 0.034	95
100% of the positive control	0.030 ± 0.004	4
The blank (row 2)	0.800 ± 0.030	/
The blank (row 11)	0.798 ± 0.027	/

Note: n=6

The mean value of optical density of the blank was 0.799 ± 0.027 . Both the left (row 2) and the right (row 11) mean of the blanks were less than 15% from the mean of all blanks.

Results and conclusions apply only to the test article tested. No further evaluation of these results was made by Shanghai Biomaterials Research & Test Center.

CONCLUSION

Under the condition of this study, the viability of 100% extract of the test article was 81 %. It can be considered that the test article extracts had not a cytotoxic potential.

RECORD STORAGE

All raw data pertaining to this study and a copy of the final report are to be stored in the designated archive files at Shanghai Biomaterials Research & Test Center.

PHOTOGRAPH OF THE TEST ARTICLE