FORMULA RECORD

Goods: Shade White Base Endurance Formula No: 7-18048

Consistency Date: 1-22-1923 Laboratory No:

For Use on Cost Classification

Code Number	One Gallon Batch				Gallon Batch			Gallon Batch			Manufacturing Specifications
	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	Gals.	Lbs.	Ozs.	
01				823/4							Grind
D43				7 7/8							Kind of Mill
1010				6 1/4							Strainer
D14				3 1/8							Weight per Gallon 15 1/2 #
											Light Baume Temp.
716					675	Changed to					Heavy Baume Temp.
711					75	750 # 716					Viscosity Temp.
7116					150						Viscosimeter
711					100						Flash Point
7169					250						Is Agitator Required
											Remarks
Yield 130											

N120

Characteristics and Method of Using	Cost Data				Customers
Type of Goods					
Color					
Luster					
Match for					
Kind of Reducer					
Amount of Reduction for					
Brushing					
Spraying — Pressure					
Dipping — Drip Time	Analysis				
Flocoing — Drip Time	Lig. 37				
Tumbling	Pig. 63				
Air dry to recoat	100				
To Sand or Rub	Liquid				
Bake Time — Temp.	Linseed Oil 89%				
Rub with	Drier 5				
Polish with	Mineral Spts. 6				
Schedule	100				
	Pigment				
	Zinc oxide 35				
	White Lead Subp. 25				
	Lithopone 20				
	Silica Silicate 20				
	100				

GLD059042