

*Obsolete
per Linda Brown
11/3/71*

FIRE-RESISTANT HYDRAULIC FLUIDS

Comparison of Physical Properties



800 North Lindbergh Boulevard
St. Louis, Missouri 63166

The information contained in this bulletin is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. Monsanto Company disclaims any liability incurred in connection with the use of these data or suggestions.

Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

0106863

TOWOLDMON0022374

WATER_PCB-00006843

PHYSICAL PROPERTIES OF

Physical Property	PYDRAUL® 60	PYDRAUL 150 (Socony-Mobil Pyrogard® 42)	PYDRAUL F-9	PYDRAUL A-200 (Shell S.F.R. Fluid 29)	PYDRAUL 625
Appearance	Cloudy Blue Liquid	Cloudy Blue Liquid	Cloudy Blue Liquid	Cloudy Blue Liquid	Cloudy Blue Liquid
Odor	Mild Ester Type	Mild Ester Type	Mild Ester Type	Mild Charac- teristic	Mild Ester Type
Specific Gravity	1.090 (75°F)	1.125 (75°F)	1.285 (75°F)	1.42 (60°F)	1.35
Viscosity (SUS) @ 100°F	62.5	143.3	235	230	628
210°F	35.1	51.6	44.7	42	45.9
Pour Point	-70°F	-55°F	-5°F	+15°F	+20°F
Flash Point	435°F	425°F	430°F	390°F	465°F
Fire Point	460°F	465°F	675°F	> 725°F	> 725°F
Autogenous Ign. Temp.	895°F	970°F	1110°F	1220°F	1080°F
Max. Temp. Tolerated For Interminant Use	200°F	200°F	300°F	300°F	300°F
Acidity	0.25 (Max)	0.17 (Max)	0.35 (Max)	0.8 to 1.10	0.35 (Max)
Type of Fluid	Phosphate Ester	Phosphate Ester Base	Phosphate Ester Base	Chlorinated Hydrocarbon Base	Phosphate Ester Base

Physical Property	Houghto-Safe† 1010	Houghto-Safe 1055	Houghto-Safe 1120	Irust® 902	Minesafe† Sunsafe†
Appearance	Light Green Liquid	Light Green Liquid	Light Green Liquid	Yellow Liquid	Liquids Sunsafe cream Minesafe-white
Odor	None	None	None	Mild Pleasant	None
Specific Gravity	1.20 (60°F)		1.15 (60°F)	0.93 (60°F)	0.92-0.93 (60°F)
Viscosity (SUS) @ 100°F	90	560	230	450 Rest	375-500
@ 210°F	38	52	43.4	253 Motion	—
Pour Point	-30°F	+25°F	- 5°F	—	0°F
Flash Point	505°F	505°F	485°F	—	—
Fire Point	670°F	675°F	670°F	—	—
Autogenous Ign. Temp.	1200°F	1200°F	1200°F	—	—
Max. Temp. Tolerated For Interminant Use	—	—	—	150°F	150°F
Acidity	0.14	—	0.1 (Max)	2.5	—
Type of Fluid	Phosphate Ester	Phosphate Ester	Phosphate Ester	Water-Oil Emulsion	Water-Oil Emulsion

*PYDRAUL is a Monsanto Company trademark. Registered in U.S. Patent Office.

0106864

TOWOLDMON0022375
WATER_PCB-00006844

FIRE-RESISTANT HYDRAULIC FLUIDS

PYDRAUL AC	Cellulube† 90	Cellulube 150	Cellulube 220	Cellulube 300	Cellulube 550
Clear Blue Liquid	Clear Oily Liquid	Clear Oily Liquid	Clear Oily Liquid	Clear Oily Liquid	Clear Oily Liquid
Mild Ester Type	Slight Mild	Slight Mild	Slight Mild	Slight Mild	Slight Mild
1.36 (60°F)	1.20-1.21 (20°C)	1.155-1.175 (20°C)	1.145-1.165 (20°C)	1.135-1.175 (20°C)	1.15-1.19 20°C
410	90	150	220	306	621
43	37	40	42	45.5	52
+20°F	-30°F	-10°F	0°F	+5°F	+20°F
470°F	455°F	455°F	455°F	455°F	455°F
> 725°F	665°F	665°F	665°F	665°F	665°F
1080°F	1150°F	1150°F	1150°F	1150°F	1150°F
350°F (Exit Air Temp.)	-	-	-	-	-
0.15 (Max)	0.1 (Max)	0.1	0.1	0.1	0.1
Phosphate Ester Base	Phosphate Ester	Phosphate Ester	Phosphate Ester	Phosphate Ester	Phosphate Ester

Celluguard 150	Celluguard† 200	Ucon† 150 CP	Ucon 275 CP	Houghto-Safe 620	
Red Liquid	Red Liquid	Cloudy Amber Liquid	Cloudy Amber Liquid	Cloudy Amber Liquid	
Characteristic	Characteristic	Characteristic	Characteristic	Characteristic	
1.055	1.060 (60°F)	1.079 (20°F)	1.08 (20°F)	1.055	
150 (76 at 150°F)	205 (102 at 150°F)	158	276	200	
-	-	-	-	-	
-25°F	-20°F	-40°F	-25°F	-60°F	
-	None	-	-	-	
-	None	-	-	-	
-	-	-	-	-	
150°F	150°F	150°F	150°F	150°F	
-	-	-	-	-	
Water, Glycol	Water/Glycol	Water/Glycol	Water/Glycol	Water/Glycol	

†These terms are registered trademarks: Celluguard & Cellulube (Stauffer Chemical Co.) Houghto-Safe (E F Houghton), Irus (Shell Oil), Minesafe & Sunsafe (Sun Oil), Pyrogard (Socony-Mobil Oil), and Uncon (Union Carbide).

0106865

Whatever their requirements, your customers get
PREVENTIVE-MAINTENANCE PROTECTION, and
DOUBLE-ACTION FIRE RESISTANCE
with a PYDRAUL hydraulic fluid.

PYDRAUL F-9
PYDRAUL A-200

for most indoor hydraulic applications that can use
a medium-viscosity fluid.

PYDRAUL 150

for outdoor, low-temperature applications,
such as Askania regulators in steel mills.

PYDRAUL 60

low-viscosity fluid for precision equipment
or very-low-temperature operation.

PYDRAUL 625

high-viscosity fluid for heavy-duty applications.

PYDRAUL AC

For air-compressor lubrication. Prevents carbon
deposits on exhaust valves and thus prevents
compressor explosions and system fires.

0106866