

PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE YE-698-D PKG

LOT F0012

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

NON-BLEEDING

PROCESSES APPROVED BY
YE-698-D (S) F. POST 9/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

PRESSING

RECORD

VAT 245
DATE 5-29-81
TIME 12:50 PM
RELEASED BY EJ
PRESS 2 92 93
NO. OF CAKES 54 54 54
PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

1ST	2ND	3RD	4TH	5TH
PRESSLOAD				
STARTED	6 PM			
CAKES USED	54			
WATER ON	9 PM			
HRS. WASHED	3			
OHMS	2300			
HRS. WASHED				
OHMS				
HRS. WASHED				
OHMS				
CAKE CONDITION				
NO CARS LOADED	7			
EXPLAIN LOSSES				

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

DRYING

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED
*No record of any processing
losses. All lumps pulled*

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED 7
SAMPLED BY RH
RELEASED BY RH

NO DRUMS 17
LUMP WGT 5238

GRINDING

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
GET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

RPM SCREEN
MAX. TEMP F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

4100
158

0.00 *

3.29 +
0.12 ✓
2.86 +
0.12 ✓
3.22 +
0.12 ✓
3.19 +
0.12 ✓
2.77 +
0.12 ✓
3.15 +
0.12 ✓
3.07 +
0.12 ✓
3.25 +
0.12 ✓
3.10 +
0.12 ✓
3.19 +
0.12 ✓
3.93 +
0.12 ✓
3.31 +
0.12 ✓
3.42 +
0.12 ✓
3.18 +
0.12 ✓
3.28 +
0.12 ✓
3.29 +
0.12 ✓
2.92 +
0.12 ✓
52.38 *