MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY908 LOT 35835

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1875	1	T- 284		
2030	1	T- 205		
	STUMP	Lump	3,773	

TOTAL NET WT. 3905 PKG. N--CODE

PROD. SPVR.	DATE	WHSE. OPER.
JV	5/30/80	

N34503

DUP050104216

23
240

MAY 19 1980

CG 03 CODE KY-908-D PKG.

→ A 23 35836

EST. WGT. 949 LBS.

TOTES OK HP

TOTAL WGT. 3549#

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-908-D (D)	EWK 12/12/77
	DCG 12/14/77
TYPED BY	
rj 1/31/78	

MAKING NOTES

REMARKS

NAME: DROLOR® YELLOW- LIGHT NON-BLEEDING

INSTRUCTIONS -PRESSING- RECORD

VAT	240				
DATE	5-23-80				
TIME	12:30 Am				
RELEASED BY	E. M.				
PRESS	2	22	23	24	
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION
WASH TO 2000 OHMS with 135-145°F water
TEST AFTER 2 HOURS
LOAD On 6 cars

AK

SAMPLES 8 oz Jar
DELIVER TO CIL for color

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	12th Noon				
CAKES USED	46				
WATER ON	5 pm				
HRS. WASHED	7				
OHMS	4070				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	7				

EXPLAIN LOSSES

SAMPLED BY #469 RELEASED BY AK

-DRYING-

DRY 24 HOURS AT 180 °F

Dry on first stage only.
Reset every 5 hrs til dry.

SAMPLES
DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATE

Color appears dry.

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12
NO. CARS PULLED 7 LUMP WGT. 3773
SAMPLED BY RELEASED BY JAR

-GRINDING-

MILL 939 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170°F

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT Can
DELIVER TO C T L

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY

DUP050104217

35.835#
41#
56#
*

332
14 –
315
14 –
332
14 –
331
14 –
323
14 –
331
14 –
30
310
14 –
322
14 –
333
14 –
312
14 –
321
14 –
349
14 –
3.773*

DUP050104218