

- 53 -

FORMULA OF SPECIFIED PAINTS AND VARNISHES
Produced by Three Manufacturers in Chicago, January 1941 - June 1942

MANUFACTURER: "A"

Varnish (12-7)

Percentage Formula	Working or Vat Formula
1941 to December 1941	January 1941 to December 1941
Percent	Gals. Lbs.
Ester Gum	50 120
"550 Durez Resin	30 30
Dehydrated Castor Oil	10
Cooked Oil	13
China Wood Oil	2
W. Body Soya	5
Zinc Acetate	12
Lead Acetate	6
Cobalt Acetate	4
Line	
Oleum	90
Spirits	50 100
	100

1942 to June 1942	January 1942 to May 1942
Percent	Gals. Lbs.
Ester Gum	40 120
Dehydrated Castor Oil	28
Cooked Oil	10
Zinc Acetate	5
China Wood Oil	16
"550 Durez Resin	30
Lead Acetate	12
Cobalt Acetate	0.5
Oleum	113
Spirits	100 100
	100

		<u>June 1942</u>	
		<u>Gals.</u>	<u>Lbs.</u>
	"A" Congo Gum		165
27	"5 Linseed	9	71.1
	Dehydrated Castor Oil	25	202
	Zinc Acetate		8
	Lead Acetate		10
	Cobalt Acetate		4
	Solv. Sol.	10	120
	Oleum	41	397

Manufacturer stated: "On the percentage formula, we only change this about once because our labels are printed up in large quantities and the minor changes do not do the physical formula a great deal."

OPA 11057

N 4973