PACKAGE TICKET (DAT AND PASTE ONLY)

CODE YC-16 LOT F1236

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	68	3400		
	STUMP	Lump	3,215	

TOTAL NET WT. 3,400 PKG. N–CODE 1000

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	5/19/81	

12/45

CG 01 CODE YC-16-B PKG. 93

→ MAY -0-81-E1236

EST. WGT. 3130 LBS.

Color in Extruder
In Box 17 Tote
on Left

OK FP

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	(A) YC-16-B	A.C 4-7-75
		JFH 5-5-75
		DCG 5-14-75
	TYPED BY	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE — NON-BLEEDING

INSTRUCTIONS						--PRESSING-- RECORD					
AT	245					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE	5-9-81					STARTED	10:50				
IME	10:40 AM					CAKES USED	34				
ELEASED BY	E.M.					WATER ON	10#				
RESS	91	92	93	2	25	HRS. WASHED	4				
O. OF CAKES	42	32	32	32	32	OHMS	3100				
RESS		AGITATION				HRS. WASHED					
ASH TO	2000	OHMS				OHMS					
EST AFTER	2	HOURS WITH 35-75 F WATER				HRS. WASHED					
OAD ON 4 CARS						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	1+3				
						EXPLAIN LOSSES					

JM

SAMPLES
DELIVER TO

SAMPLED BY RELEASED BY JM

--DRYING--

DRY 16 HOURS AT 220 F

LUMP: - OK - WET - SALTS - CONTAMINATED

DRYER SECTIONS USED:

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 3215

SAMPLED BY RELEASED BY JM

--GRINDING--

MICROATOMIZE
SET ROOF GATE AT 5 INCHES AIR FLOW
MAGNEHELIC READING ON ATOMIZER PANEL 1.0"

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050096184

Vc-16 B

1236
4100
158

0.00 *

2.73 +
0.12 -
2.75 +
0.12 -
2.84 +
0.12 -
7.96 *

7.96 +
3.06 +
0.12 -
2.91 +
0.12 -
2.93 +
0.12 -
3.08 +
0.12 -
2.96 +
0.12 -
3.10 +
0.12 -
2.91 +
0.12 -
2.64 +
0.12 -
1.68 +
0.12 -
32.15 *