

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 150 909 LOT 34074

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>2,520</u>	<u>1</u>	<u>T-</u>	<u>105</u>	
<u>2,355</u>	<u>1</u>	<u>T-</u>	<u>2</u>	

STUMP

TOTAL NET WT. 4,875 PKG. N-CODE _____

PROD. SPVR.

DATE

WHSE. OPER.

JV

2/3/80

CG 04 CODE KO-909-D PKG. _____

→ JAN 30 34074
EST. WGT. 1674/530 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KO-909-D (C) APPROVED BY
EWK 1-27-78
DCG 1-30-78TYPED BY
NSA 3-13-78
MAKING NOTES

REMARKS

TOTAL WGT. 5274 (Req _____)

NAME: KROLOR® ORANGE Y

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT					247 3-1-80 2:10P 55 48	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE						STARTED	132 PM				
TIME						CAKES USED	48				
RELEASED BY						WATER ON	5:00 PM				
PRESS	2	22	23	24	25	HRS. WASHED	18				
NO. OF CAKES	46	46	46	52	48	OHMS	3500				
PRESS with						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER						HRS. WASHED					
LOAD	on 6 cars					OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES 18 oz
DELIVER TO CTL for color

SAMPLED BY 169 RELEASED BY TDS

- DRYING -

DRY 22 HOURS AT 180°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNO. DRUMS 20
LUMP WGT. 5024
RELEASED BY

- GRINDING -

MILL 938 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170°FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO CTLDATE MIXED
SAMPLED BY RELEASED BY

DUP050094186

N 26400.01

34074
41
16

0.00 *

34074
41
371

0.00 *

0.00 *

2.73 +

0.12 -

2.69 +

0.12 -

2.77 +

0.12 -

2.70 +

0.12 -

2.77 +

0.12 -

2.72 +

0.12 -

2.65 +

0.12 -

2.69 +

0.12 -

2.73 +

0.12 -

2.70 +

0.12 -

2.59 +

0.12 -

2.67 +

0.12 -

2.76 +

0.12 -

2.68 +

0.12 -

2.73 +

0.12 -

2.67 +

0.12 -

41.33 *

2.76 +

0.14 -

2.75 +

0.14 -

2.64 +

0.14 -

1.32 +

0.14 -

41.33 +

50.24 *