REGISTERED
REG'N. No. 7513
DATE 5-1

O'BRIEN

"SEVENTY-FIVE"®
Gloss
HOUSE PAINT

CC WHITE

Controlled Chalking
(Formerly Trim & Tinting White)

ONE GALLON

"SEVENTY-FIVE" GLOSS HOUSE PAINT

(Formerly "75" House Paint)

"75" House Paint is a premium quality, modified linseed oil gloss paint for exterior use. Ideal for repainting prefinished aluminum siding. Available in Priming White, standard colors, and three types of finish white: self-cleaning White; CC White for Controlled Chalking—trim work, etc.; and White Bases No. 1, 2, and 3 (for tinting only) for body or trim work.

DIRECTIONS

Preparation — Remove dirt, chalk, and loose paint. Repair flashings, caulk, provide adequate ventilation for release of moisture. Sand under eaves and protected areas, **wash with detergent and thoroughly rinse.**

Priming — *Unless badly weathered, prefinished aluminum siding does not* require priming. Prime new wood, and prime or spot prime previous paint in poor condition with "75" House Paint Priming White. Prime new masonry with alkali-resistant "A-R" Primer. Prime bare metal with Flexico Metal Primer. Etch galvanized metal before priming. Tint primers toward topcoat color.

Tinting — Tint White Bases No. 1, 2, and 3 with Tone-All Universal Tinting Colors according to O'Brien Symphonic Color System formulas. Do not use alkali-sensitive colorants Orange, Medium Yellow, and Medium Green on masonry surfaces unless sealed with alkali-resistant primer.

Application — Stir well. Apply over a dry surface at temperature not less than 60° F. If thinning is desired, use turpentine or mineral spirits up to one-half pint per gallon for brush application. For spray, thin with light naphtha 1 pint per gallon. Avoid painting in damp weather or late in the evening. *Allow 48 hours good drying weather between coats.*

SPECIAL: Enamelized Trim Colors—Hard-finish, faster drying colors for **trim use only.** Do not prime with conventional house paint primer. Use as a self-primer over new wood, by reducing 1st coat with one pint of turpentine or mineral spirits per gallon. Apply at package consistency over previous paints. — (PYOW)

CAUTION! COMBUSTIBLE! CONTAINS LEAD. HARMFUL IF SWALLOWED. Keep away from heat and open flame. Do not apply on window sills, toys, furniture or interior surfaces of rooms which may be used by children. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use. Use with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN.

75 HOUSE PAINT
TRIM AND TINTING WHITE

*Pigment	56.68%
Titanium Dioxide	24.03%
18% Leaded Zinc Oxide	38.96%
Silicates	37.01%
	100.00%
*Vehicle	43.32%
Raw Linseed Oil	44.10%
Heat Treated Linseed Oil	27.35%
Thermolyzed Tung Oil	2.74%
Mineral Spirits & Driers	25.81%
	100.00%

SINCE O'BRIEN 1875

MADE BY THE O'BRIEN CORPORATION

SOUTH BEND IND • BALTIMORE MD • OKLAHOMA CITY OKLA • LOS ANGELES CAL • BRUNSWICK GA

49 TOC 001762

REGISTERED
REG'N. No. 75138
DATE 5-13-68

O'BRIEN

"SEVENTY-FIVE"®
Gloss
HOUSE PAINT

CREAM

ONE GALLON

49 TOC 001763

"SEVENTY-FIVE" GLOSS HOUSE PAINT

(Formerly "75" House Paint)

"75" House Paint is a premium quality, modified linseed oil gloss paint for exterior use. Ideal for repainting prefinished aluminum siding. Available in Priming White, standard colors, and three types of finish white: self-cleaning White; CC White for Controlled Chalking—trim work, etc.; and White Bases No. 1, 2, and 3 (for tinting only) for body or trim work.

DIRECTIONS

Preparation — Remove dirt, chalk, and loose paint. Repair flashings, caulk, provide adequate ventilation for release of moisture. Sand under eaves and protected areas, **wash with detergent and thoroughly rinse.**

Priming — Unless badly weathered, prefinished aluminum siding does not require priming. Prime new wood, and prime or spot prime previous paint in poor condition with "75" House Paint Priming White. Prime new masonry with alkali-resistant "A-R" Primer. Prime bare metal with Flexico Metal Primer. Etch galvanized metal before priming. Tint primers toward topcoat color.

Tinting — Tint White Bases No. 1, 2, and 3 with Tone-All Universal Tinting Colors according to O'Brien Symphonic Color System formulas. Do not use alkali-sensitive colorants Orange, Medium Yellow, and Medium Green on masonry surfaces unless sealed with alkali-resistant primer.

Application — Stir well. Apply over a dry surface at temperature not less than 60° F. If thinning is desired, use turpentine or mineral spirits up to one-half pint per gallon for brush application. For spray, thin with light naphtha 1 pint per gallon. Avoid painting in damp weather or late in the evening. Allow 48 hours good drying weather between coats.

SPECIAL: Enamelized Trim Colors—Hard-finish, faster drying colors for **trim use only.** Do not prime with conventional house paint primer. Use as a self-primer over new wood, by reducing 1st coat with one pint of turpentine or mineral spirits per gallon. Apply at package consistency over previous paints.

— (PYOW)

CAUTION! COMBUSTIBLE! CONTAINS LEAD. HARMFUL IF SWALLOWED. Keep away from heat and open flame. Do not apply on window sills, toys, furniture or interior surfaces of rooms which may be used by children. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use. Use with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN.

"75" HOUSE PAINT TINT BASE

Pigment	56.66%
Titanium Dioxide	9.84%
Titanium Calcium Pigment	22.95%
18% Leaded Zinc Oxide	36.07%
Magnesium Silicate	31.14%
	100.00%
Vehicle	43.34%
Raw Linseed Oil	41.69%
Heat Treated Linseed Oil	26.84%
Thermolyzed Tung Oil	2.76%
Mineral Spirits and Driers	28.71%
	100.00%

Less Than 5% Tinting Colors Added

SINCE O'BRIEN 1875

MADE BY THE O'BRIEN CORPORATION

SOUTH BEND IND • BALTIMORE MD • OKLAHOMA CITY OKLA • LOS ANGELES CAL • BRUNSWICK GA

49 TOC 001764

REGISTERED
REG'N. No. 75313
DATE 5/13/68

O'BRIEN

"SEVENTY-FIVE"®
Gloss
HOUSE PAINT

IVORY

ONE GALLON

49 TOC 001765

"SEVENTY-FIVE" GLOSS HOUSE PAINT

(Formerly "75" House Paint)

"75" House Paint is a premium quality, modified linseed oil gloss paint for exterior use. Ideal for repainting prefinished aluminum siding. Available in Priming White, standard colors, and three types of finish white: self-cleaning White; CC White for Controlled Chalking—trim work, etc.; and White Bases No. 1, 2, and 3 (for tinting only) for body or trim work.

DIRECTIONS

Preparation — Remove dirt, chalk, and loose paint. Repair flashings, caulk, provide adequate ventilation for release of moisture. Sand under eaves and protected areas, **wash with detergent and thoroughly rinse.**

Priming — Unless badly weathered, prefinished aluminum siding does not require priming. Prime new wood, and prime or spot prime previous paint in poor condition with "75" House Paint Priming White. Prime new masonry with alkali-resistant "A-R" Primer. Prime bare metal with Flexico Metal Primer. Etch galvanized metal before priming. Tint primers toward topcoat color.

Tinting — Tint White Bases No. 1, 2, and 3 with Tone-All Universal Tinting Colors according to O'Brien Symphonic Color System formulas. Do not use alkali-sensitive colorants Orange, Medium Yellow, and Medium Green on masonry surfaces unless sealed with alkali-resistant primer.

Application — Stir well. Apply over a dry surface at temperature not less than 60° F. If thinning is desired, use turpentine or mineral spirits up to one-half pint per gallon for brush application. For spray, thin with light naphtha 1 pint per gallon. Avoid painting in damp weather or late in the evening. Allow 48 hours good drying weather between coats.

SPECIAL: Enamelized Trim Colors—Hard-finish, faster drying colors for **trim use only.** Do not prime with conventional house paint primer. Use as a self-primer over new wood, by reducing 1st coat with one pint of turpentine or mineral spirits per gallon. Apply at package consistency over previous paints.

CAUTION! COMBUSTIBLE! CONTAINS LEAD. HARMFUL IF SWALLOWED. Keep away from heat and open flame. Do not apply on window sills, toys, furniture or interior surfaces of rooms which may be used by children. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use. Use with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN.

"75" HOUSE PAINT TINT BASE

Pigment	56.66%
Titanium Dioxide	9.84%
Thorium Calcium Pigment	22.93%
18% Leaded Zinc Oxide	36.07%
Magnesium Silicate	31.14%
	100.00%
Vehicle	43.34%
Raw Linseed Oil	41.69%
Heat Treated Linseed Oil	26.84%
Thermolyzed Tung Oil	2.76%
Mineral Spirits and Driers	28.71%
	100.00%

Less Than 5% Tinting Colors Added

— (PYOW)

SINCE O'BRIEN 1875

MADE BY THE O'BRIEN CORPORATION

SOUTH BEND IND • BALTIMORE MD • OKLAHOMA CITY OKLA • LOS ANGELES CAL • BRUNSWICK GA

49 TOC 001796

REGISTERED
REG'N. No. 7573B
DATE 5-13-68

O'BRIEN

"SEVENTY-FIVE"®
Gloss
HOUSE PAINT

WHITE

ONE GALLON

49 TOC 001767

"SEVENTY-FIVE" GLOSS HOUSE PAINT

(Formerly "75" House Paint)

"75" House Paint is a premium quality, modified linseed oil gloss paint for exterior use. Ideal for repainting prefinished aluminum siding. Available in Priming White, standard colors, and three types of finish white: self-cleaning White; CC White for Controlled Chalking—trim work, etc.; and White Bases No. 1, 2, and 3 (for tinting only) for body or trim work.

DIRECTIONS

Preparation — Remove dirt, chalk, and loose paint. Repair flashings, caulk, provide adequate ventilation for release of moisture. Sand under eaves and protected areas, **wash with detergent and thoroughly rinse.**

Priming — Unless badly weathered, prefinished aluminum siding does not require priming. Prime new wood, and prime or spot prime previous paint in poor condition with "75" House Paint Priming White. Prime new masonry with alkali-resistant "A-R" Primer. Prime bare metal with Flexico Metal Primer. Etch galvanized metal before priming. Tint primers toward topcoat color.

Tinting — Tint White Bases No. 1, 2, and 3 with Tone-All Universal Tinting Colors according to O'Brien Symphonic Color System formulas. Do not use alkali-sensitive colorants Orange, Medium Yellow, and Medium Green on masonry surfaces unless sealed with alkali-resistant primer.

Application — Stir well. Apply over a dry surface at temperature not less than 60° F. If thinning is desired, use turpentine or mineral spirits up to one-half pint per gallon for brush application. For spray, thin with light naphtha 1 pint per gallon. Avoid painting in damp weather or late in the evening. Allow 48 hours good drying weather between coats.

SPECIAL: Enamelized Trim Colors—Hard-finish, faster drying colors for **trim use only.** Do not prime with conventional house paint primer. Use as a self-primer over new wood, by reducing 1st coat with one pint of turpentine or mineral spirits per gallon. Apply at package consistency over previous paints. — (PYOW)

CAUTION! COMBUSTIBLE! CONTAINS LEAD. HARMFUL IF SWALLOWED. Keep away from heat and open flame. Do not apply on window sills, toys, furniture or interior surfaces of rooms which may be used by children. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use. Use with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN.

"75" HOUSE PAINT — WHITE

Pigment	59.99%
Titanium Dioxide	16.33%
Titanium Calcium Pigment	20.41%
Basic Carbonate White Lead	2.62%
18% Leaded Zinc Oxide	34.99%
Zinc Oxide	4.66%
Magnesium Silicate	20.99%
	100.00%
Vehicle	40.01%
Raw Linseed Oil	46.90%
Heat Treated Linseed Oil	19.48%
Thermolyzed Tung Oil	2.82%
Mineral Spirits & Driers	30.80%
	100.00%

SINCE O'BRIEN 1875

MADE BY THE O'BRIEN CORPORATION

SOUTH BEND IND • BALTIMORE MD • OKLAHOMA CITY OKLA • LOS ANGELES CAL • BRUNSWICK GA

49 TOC 001768