

PACKAGE NO. 1

CODE 24 695 LOT 38457

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	<u>11</u>	<u>13/10</u>	<u>34</u>	

STUMP Lump 10.49

TOTAL NET WT. 151.2 PKG. N-CODE

PROD. SPVR. DATE 1/16/71 WHSE. OPER.

D. T

1.6. +

1.0. +

1.2. +

1.1. +

1.1. +

1.7. +

1.4. +

1.1. +

1.0. +

1.6. +

1.4. +

13.2. T

CG 36 CODE RT-695-D PKG.
 → DEC: 23 80 38437
 EST. WGT. 1350 LBS.

(1B)

PROCESSING INSTRUCTIONS: BATCH UNIT

36 102	PROCESSES RT-695-D (M)	APPROVED BY DCG 1-12 IHD 2-25
	TYPED BY LG 5-15-72	
	MAKING NOTES	
	REMARKS	

Retyped 2-27-80
Mm

NAME: BON RED DARK

NON-BLEEDING

INSTRUCTIONS						-PRESSING-		RECORD				
VAT	107					PRESSLOAD	1ST	2ND	3RD	4TH	5TH	
DATE	12-28-80					STARTED	12:01 PM					
TIME	10:45 PM					CAKES USED	32					
RELEASED BY	244					WATER ON	9:30 AM					
PRESS	2236	33	35	38	39	HRS. WASHED	17:14					
NO. OF CAKES	30	60	60	60	60	OHMS	150					
PRESS Without		AGITATION				HRS. WASHED						
WASH TO	4000	OHMS with 35-75F water				OHMS						
TEST AFTER	16	HOURS				HRS. WASHED						
LOAD	on 8 cars					OHMS						
						CAKE CONDITION						
						NO. CARS LOADED	34					
						EXPLAIN LOSSES						
SAMPLES	803											
DELIVER TO						SAMPLED BY		RELEASED BY	OK			

-DRYING-

HOURS Dry 24 hours at	L.V.	H.V.	LUMP: - OK - WET - SALTS - CONTAMINATE
TEMP.	180 °F	°F	
SE	15-30		No record of any color losses
Mn Color			in processing Released 1/6/81
			ADDITIONAL DRYING HOURS REQUIRED
SAMPLES	803		Drums 8
DELIVER TO		NO. CARS PULLED	LUMP WGT. 1249
		SAMPLED BY	RELEASED BY OK

-GRINDING-

MILL 5 HSP 1/8" RP	SCREEN 4600	RPM	SCREEN	RPM
MAX. TEMP.	°F		MAX. TEMP.	°F
Mn Color				
			EXPLAIN LOSSES	
SAMPLE AFTER / WITHOUT MIXING			DATE MIXED	1/6/81
SAMPLES Env & 2 pc cans			SAMPLED BY	27/10/81
ELIVER TO CTL			RELEASED BY	

38437
51
231

0.00 *
180.00 +
14.00 -
190.00 +
14.00 -
195.00 +
14.00 -
185.00 +
14.00 -
195.00 +
14.00 -
120.00 +
14.00 -
981.00 *

360

38437
51
16

0.00 *

9.81 +
2.00 +
0.14 -
0.96 +
0.14 -
12.49 *

100