

93 MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE K7-787 LOT 38292

NET WT/PKG	NO. PKG	FACIL. INST	LOCATION	PQ
1670	1	T-152		
1410	1	T-252		
[redacted]		LJKNP	3261	

TOTAL NET WT. 3080 PKG. N-CODE

PROD. SPVR. SAI DATE 12 22 80 WHSE. OPER.

N34739

23/240

CG 03 CODE KY-787-D PKG. ____

→ DEC 17 80 38292

EST. WGT. ~~1090~~ 937 LBS.

3332

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-787-D (Q)	EWK 9/22/76
		DCG 9/27/76
	RETYPED BY	
	CJH 4/2/80	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM — NON-BLEEDING

-PRESSING-

INSTRUCTIONS					RECORD					
VAT	249				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	12-18-80				STARTED	4 AM				
TIME	2:50 A M				CAKES USED	46				
RELEASED BY	C. M.				WATER ON	9				
PRESS	22	23	24	25	HRS. WASHED	6				
NO. OF CAKES	46	46	52	48	OHMS	3200				
PRESS WITH		AGITATION			HRS. WASHED					
WASH TO 2000		OHMS WITH 35-75 F WATER			OHMS					
TEST AFTER 2		HOURS			HRS. WASHED					
LOAD ON 6 CARS					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	6				
					EXPLAIN LOSSES					

SAMPLES 1-8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY — RELEASED BY

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

No record of any losses in Processing / Release 12-20-80

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 13

SAMPLES
DELIVER TO

NO. CARS PULLED — LUMP WGT. 3261
SAMPLED BY — RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM	SCREEN RPM
MAX. TEMP. 150 °F	MAX. TEMP. °F
	EXPLAIN LOSSES
SAMPLE AFTER / WITHOUT MIXING	DATE MIXED
SAMPLES 1 ENV & 1 PT. CAN	
DELIVER TO CTL	SAMPLED BY — RELEASED BY

DUP050105139

38292
41
16

0.00	
2.70	
0.12	-
2.64	+
0.12	-
2.59	+
0.12	-
2.62	+
0.12	-
2.70	+
0.12	-
2.59	+
0.12	-
2.78	+
0.12	-
2.69	+
0.12	-
2.72	+
0.12	-
2.75	+
0.12	-
0.12	-
2.79	+
0.12	-
2.76	+
0.12	-
1.84	*
32.61	*
0.00	*

DUP050105140