MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY 787 LOT 33303

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	69	3,450		
	STUMP			

TOTAL NET WT. 3,450 PKG. N–CODE 1130

PROD. SPVR. DM DATE 1',2,80 WHSE. OPER.

23/244

CG 03 CODE KY-787-D PKG. ____

→ DEC 28 33503

EST. WGT. 1090 LBS.

OK
KP

Total Wgt. 3490#

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (R)	EWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NE 2/12/77	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
VAT		244			
DATE		12-28-79			
TIME		11:50A			
RELEASED BY		[illegible]			
PRESS	22	23	24	24	
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION

WASH TO 2000 OHMS with 35-75°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

S.K.

SAMPLES 1-8 oz JAR

DELIVER TO ctl for color

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1PM				
CAKES USED	46				
WATER ON	352				
HRS. WASHED	5				
OHMS	2100				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY #401 RELEASED BY S.K.

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 16

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 352

SAMPLED BY RELEASED BY BLL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 ENV & 1 Pt. can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050093347

N 26201.01

DUP050093348