

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

150786

LOT

33572

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

2470

1

T-

1-3

2500

1

T-

1-2

STUMP

TOTAL NET WT.

4770

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

JH

1/15/80

24
24/6
04 CODE KO-786-D PKO.
DEC 20 33572
EST. WGT. 862 LBS.

OK
H

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KO-786-D (P)
APPROVED BY
EWK 9-21-76
DCG 9-21-76

TYPED BY
jlc 11-15-76

MAKING NOTES

REMARKS

Received at 7:45 pm

TOTAL WEIGHT 4962 (Req. _____)

NAME: "KROLOR" ORANGE R

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT 246
DATE 12-20-76
TIME 3:30 PM
RELEASED BY
PRESS 22 23 24 25
NO. OF CAKES 46 46 52 48
PRESS with AGITATION
WASH TO 5000 OHMS with 35-75°F water
TEST AFTER 6 HOURS
LOAD on 6 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7:45 PM				
CAKES USED	52				
WATER ON	12:00 PM				
HRS. WASHED	8				
OHMS	5700				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	5				
EXPLAIN LOSSES					

SAMPLES 1-8 oz. jar
DELIVER TO Ctl for color

SAMPLED BY #12 RELEASED BY A.R.

-DRYING-

DRY 16 HOURS AT 220°F L.V.
TEMP.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS: 15
LUMP WGT. 9821
RELEASED BY

-GRINDING-

MILL 938 HSP 3/32" SCREEN 3500 RPM
MAX. TEMP. 210°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. + 1 Pint Can
DELIVER TO Ctl

DATE MIXED

SAMPLED BY

RELEASED BY

33572
51
158

0.00 *
3.22 +
0.14 -
2.92 +
0.14 -
3.13 +
0.14 -
3.63 +
0.14 -
3.22 +
0.14 -
4.12 +
0.14 -
19.45 *
0.00 *

33572
51
16

0.00 *
0.00 *
19.45 +
3.22 +
0.14 -
3.30 +
0.14 -
3.62 +
0.14 -
3.25 +
0.14 -
3.69 +
0.14 -
3.70 +
0.14 -
3.40 +
0.14 -
3.47 +
0.14 -
2.22 +
0.14 -
4.21 *