MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE AT-695-1 LOT 24702

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1212	10	1212	42-35	

1@1212 STUMP

TOTAL NET WT. 1212 PKG. N-CODE

PROD. SPVR. DATE WHSE. OPER.

3/14/80 74

32
V104

CG 36 CODE RT-695-D PKG. ____

→ MAR-4 34702

EST. WGT. 1350 LBS.

2 Dr

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-695-D (M)	DCG 1-12
	IHD 2-25
TYPED BY	
LG 5-15-72	

~~Retyped 2-27-80~~ MnM

MAKING NOTES

REMARKS

NAME: BON RED DARK

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	107					STARTED	1st DM				
DATE	3/6/80					CAKES USED	30				
TIME	8.45PM					WATER ON	1.AM				
RELEASED BY						HRS. WASHED	9				
PRESS	32	33	35	38	39	OHMS	4000				
NO. OF CAKES	30	60	60	60	60	HRS. WASHED					
PRESS Without AGITATION						OHMS					
WASH TO 4000 OHMS with 35-75F water						HRS. WASHED					
TEST AFTER 16 HOURS						OHMS					
LOAD on 8 cars						CAKE CONDITION	2T				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

AK

SAMPLES
DELIVER TO

SAMPLED BY RELEASED BY CC

-DRYING-

HOURS Dry 24 hours at L.V. , H.V.
TEMP. 180 °F °F
SE 15-30
Mn Color

LUMP: - OK - WET - SALTS - CONTAMINATE

No Record of any Processing losses

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 7
SAMPLED BY RELEASED BY

-GRINDING-

MILL 5 HSP 1/8" RP SCREEN 4600 RPM
MAX. TEMP. °F
Mn Color

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES


SAMPLE AFTER / WITHOUT MIXING
SAMPLES Env & 2 pt cans
DELIVER TO C T L

DATE MIXED 4-8-80

SAMPLED BY RELEASED BY


DUP050292561

N 31859.01



DUP050292562

N 31859.02



DUP050292563

N 31859.03