

VISCOSITY WORK SHEET

Item <u>1428</u>	P.T.No. _____	Date <u>2/23/54</u>
Worker <u>Jackie Harrison</u>	Polymer <u>Lucite</u>	Solvent <u>EDC</u>
For <u>Squire</u>	Charge <u>1244</u>	Temperature _____
Viscometer No. <u>1</u>	Efflux Time <u>236.3</u>	Weight: Gross _____
Viscometer No. <u>2</u>	Efflux Time <u>219.8</u>	Tare _____
Viscometer No. _____	Efflux Time _____	Net _____

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Inh. visc. Visc. or M.W.	
4339-14	50A	1	355.5, 355.5	1.501	0.81
	520	2	329.8, 330.2, 330.1, 330.4, 330.1	1.501	0.81