

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE YT808 LOT 38/03

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
------------	---------	-----------	----------	----

13 1968 43

[illegible]

STUMP 122 m/f 1985

TOTAL NET WT. 1985 PKG. N-CODE _____

PROD. SPVR.	DATE	WHSE. OPER.

D. T

161. +
178. +
163. +
164. +
156. +
164. +
158. +
160. +
171. +
175. +
165. +
167. +
176. +
1988. T

N35210

CG 46 CODE YT-808-D PKG.
 → DEC -2 80 38103
 EST. WGT. 2238 LBS.

90"
 168°

231

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YT-808-D (D)	ENK 9/28/77
	BGR 10/17/77
	ECG 10/17/77
TYPED BY	
JTC 10/26/77	
MAKING NOTES	

REMARKS

AME: DALAMAR® YELLOW BLEEDING

INSTRUCTIONS				- PRESSING -	RECORD				
AT				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE				STARTED	12:30 PM				
IME				CAKES USED	62				
RELEASED BY				WATER ON	2:30 PM				
RESS	32	33	35	MRS. WASHED	4 1/2				
NO. OF CAKES	60	62	60	OHMS	4000				
RESS	WITHOUT			MRS. WASHED		Start 3:00 PM			
ASH TO	4000	OHMS with 35-75°F water			OHMS	FIN. 11:40			
EST AFTER	4	HOURS			MRS. WASHED				
OAD	on 9 cars			OHMS		2:10			
				CAKE CONDITION	5				
				NO. CARS LOADED					
				EXPLAIN LOSSES					

AMPLES DELIVER TO
 SAMPLED BY
 RELEASED BY

- DRYING -
 DRY 24 HOURS AT 200°F
 LUMP: - OK - WET - SADS - CONTAMINATED
 No Record of any processing losses.
 ADDITIONAL DRYING HOURS REQUIRED

AMPLES DELIVER TO
 NO. CARS PULLED
 SAMPLED BY
 RELEASED BY

- GRINDING -
 MILL 4 or 10 HSP 1/8" RBCREEN 3500 RPM
 MAX. TEMP. 190 °F
 SCREEN RPM
 MAX. TEMP. °F
 EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
 SAMPLES 1 env + 1 Pint can
 DELIVER TO C T L
 DATE MIXED 12/4/80
 SAMPLED BY 2/3
 RELEASED BY

DUP 5 CAPS 12000000

1

38100
124
51
124
14
136
14
137
14
192
14
179
14
193
14
181
14
187
14
180
14
186
14
176
14
124
14
175