

CG 03 CODE KY-787-D PKG.
→ DEC-17 80 38291
EST. WGT. 1000 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES KY-787-D (Q)	APPROVED BY EWK 9/22/76 DCG 9/27/76
RETYPE BY CJH 4/2/80	
MAKING NOTES	

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	240					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	12-18-80					STARTED	3:18				
TIME	11:55AM					CAKES USED	52				
RELEASED BY	S.R.					WATER ON	10 PM				
PRESS	22	23	24	25		HRS. WASHED	2				
NO. OF CAKES	46	46	52	48		OHMS	2000				
PRESS WITH						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 2						HRS. WASHED					
LOAD ON 6 CARS						OHMS					

SAMPLES 1-8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY RELEASED BY

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

COLOR APPEARED DR. /
RELEASED 12/20/80

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYLUMP WGT. 3497
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT. CAN
DELIVER TO C.T.L.

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050105145

38291
4100
18

0.00 *
2.61 +
0.14 -
2.90 +
0.14 -
2.79 +
0.14 -
2.92 +
0.14 -
2.90 +
0.14 -
2.86 +
0.14 -
2.65 +
0.14 -
2.71 +
0.14 -
2.77 +
0.14 -
2.84 +
0.14 -
2.54 +
0.14 -
3.03 +
0.14 -
31.84 *

38291
41
16

0.00 *

31.84 +
2.77 +
0.14 -
34.47 *