SECTION II-A-2.1

INSULATION MATERIALS

MASTICS AND COATINGS

EMULSION TYPE

Lagtones

30-70
31-80
31-90
31-95
31-49

Composition

A non-toxic, tough, flexible fire-resistive polyvinyl acetate based emulsion containing fillers and pigments.

When dry, it has good resistance to weather, dilute acids, alkalies, solvents and water.

Colors

30-70: White
31-80: Buff
31-90: Gray
31-95: Black
31-49: Aluminum gray

Viscosity

All: Fluid

Application Method

All: Brush

Coverage

All: 50 to 60 sq.ft./gal. - 1.32" wet film thickness

Drying Time

Touch: 1 hour
Through: 4 hours

Temperature Limits

Insulation surface: -50°F to +180°F

Flammability

Wet: Non-flammable
Dry: Self-extinguishing