

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

85615

LOT

31528

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

8

804

20

STUMP

Lumber 160

TOTAL NET WT.

804

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

JH

10/28/80

2-3

Q.T.

114.+

107.+

99.+

88.+

103.+

96.+

111.+

88.+

804.T

36/100 CG 36 CODE RT-695-D PKG.
OCT. 20 80 38528
EST. WGT. 0 LBS.

STUMP PRESS - 18 CAKES

363
TOTAL WEIGHT 1016

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES APPROVED BY

TYPED BY

MAKING NOTES

REMARKS

NAME: "BON" RED DARK

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT.	100				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	10.20.80				STARTED	4 PM				
TIME	1354				CAKES USED	13				
RELEASED BY					WATER ON	10 PM				
PRESS	36				HRS. WASHED	15				
NO. OF CAKES	18				OHMS	5000				
PRESS WITH					HRS. WASHED					
WASH TO 8000					OHMS					
TEST AFTER 4					HRS. WASHED					
LOAD	on 4 cars				OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	1				
					EXPLAIN LOSSES					

AGITATION
OHMS with 135-145°F water
HOURS

then washed to 5000 OHMS only -
only water low
on my f.s.W

SAMPLES 803 - R & D
DELIVER TO

SAMPLED BY 85 RELEASED BY VW

-DRYING-

DRY. 24 HOURS AT 180°F
Mn color

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 803 R & D
DELIVER TO

NO. CARS PULLED 1
SAMPLED BY

NO. DRUMS 5
LUMP WGT. 760
RELEASED BY 131

-GRINDING-

MILL #5 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F
Mn color

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES env & 2 pt chgs
DELIVER TO CTL

DATE MIXED
SAMPLED BY

RELEASED BY

TAKEN WK
10/28

37258
51
69

0.00 *

1.98 +

0.14 -

2.02 +

0.14 -

1.92 +

0.14 -

1.88 +

0.14 -

0.50 +

0.14 -

7.60 *

7.60M+