MO-8-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE 2-1-13 LOT 3-5712

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
12.5	17	212.5		
STUMP				

TOTAL NET WT. 212.5 PKG. N-CODE 45-52

PROD. SPVR. DATE WHSE. OPER.

5-12-8

N32285

DUP050457404

35/204

MAY 8 1980

CG 08 CODE A-143-D PKG.

→ NAY12 35712

EST. WGT. 2184 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

MFS

PROCESSES	APPROVED BY
A-143-D (E)	JJ 06 08 78
	JJG 05 07 79
	JJG 5/8/79
re TYPED BY	
emw050779	

MAKING NOTES

REMARKS

NAME: CARBON BLACK

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT		204				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		5-13-80				STARTED	1.30A				
TIME		910/PM				CAKES USED	60				
RELEASED BY		AJM				WATER ON	3 15/A				
PRESS	~~20~~	21				HRS. WASHED	5				
NO. OF CAKES	2x48	2x32				OHMS	5000				
PRESS	with	AGITATION				HRS. WASHED					
WASH TO	4000	OHMS with 35-75°F water				OHMS					
TEST AFTER	2	HOURS				HRS. WASHED					
LOAD	on 6 cars					OHMS					
	Ask Making to reheat to 180-185°F					CAKE CONDITION					
	before pressing					NO. CARS LOADED	1+5				
						EXPLAIN LOSSES					

SAMPLES

DELIVER TO

SAMPLED BY RELEASED BY

-DRYING-

Dry 30 hours at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 17

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 2254

SAMPLED BY RELEASED BY

-GRINDING-

MILL #7 HSP SCREEN 3/32" RPM 3500

MAX. TEMP. 210°F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER MIXING into new drums

SAMPLES 2 Env, 2 Pt Cans, 3 Qt Jars

DELIVER TO CTL

DATE MIXED 5/28/80

SAMPLED BY #153 RELEASED BY

N32285.01

DUP050457405

357.12N
.51N
3.24N
.00T

1.44
.14-
1.49
.17-
1.47
.14-
1.54
.14-
1.63
.17-
1.62
.14-
1.66
.17-
1.56
.14-
1.69
.17-
1.38
.14-
1.48
.17-
1.45
.14-
1.45
.14-
1.23
.14-
.89
.14-
19.73T

1/2 wet car

357.12N
.51N
2.25N
.00T

1.50
.12-
1.60
.17-
2.81T
1973
2254

N32285.02

DUP050457406