

FORMULA RECORD			6	AIR 5
CONTROL LAB Cleveland T. S.			DATE 4-4-52	REL NO. 459
NAME S W P Berkley Yellow			CARD NO. 16	
POUNDS	GALLONS	MATERIAL NO.	CUSTOMER Sherwin-Williams Co.	
200	8.4	20 or 312	TO MATCH Neutral Oil Standard #85	
350	12.9	2140		
300	6.2	412 or 413	REASON FOR REVISION Reducing total loaded	
100	2.1	6802 or 1424	or zinc (Zinc-226 min.)	
		6828		
20	1.1	BY 10		
2(2)	.1	BY 20	VISCOSITY 20-30-75	
2		BO 30	VISCOSITY on #3 oil	
			% SOLIDS (RUN)	
4	1/2	(5094)	ROYALTY YES/NO	
251	32 1/2	(2)	WT./GAL T 14.79	
153	19	(310)	LABEL ANALYSIS CHECKED G	
			BAUME	
			LBS. OR GALS. PER HOUR	
9	1 1/4	(1230)	DEPARTMENT	
5	3/4	(543)	PACKAGE	
27	4	(141)	APPROVED	
85	13	(348)	FORMULATOR	
			PARALLEL NO.'S	
			No Parallel	
			SUIT	

N16351

0007-SWP-063067

MANUFACTURING INSTRUCTIONS. 1. GALS OF (798)			MAY REPLACE 1 GALS OF (2) TO IMPROVE		
FLOW.			NO. COATS		
APPLICATION SURFACE Wood etc.			UNDERCOATER USED 1x 150		
METHOD 1. Brush			REDUCER USED		
REDUCER AMOUNT			REDUCER USED		
REDUCER AMOUNT			REDUCER USED		
DRYING TIME, TOUCH-DRY RECOAT 2-4 days			SAND		
TACK FREE			RUB		
EVENING TIME AND TEMP.			FILM		
GLOSS 0.1			SPECIAL TESTS		
MEXICO			RES ADM		
BRAZIL			S		
BUENOS AIRES			Z		
MONTREAL			G		
CUBA			H		
EXEC. MFG.			F		
GIBBSBORO			I		
DAYTON			T		
DALLAS			P		
LOS ANGELES			D		
DETROIT			M		
H. SENOUR			O		
OAKLAND			N		
NEWARK			KENS. LACQUER		
KENS. TECH. SERV.			ALLIED RESEARCH		
KENSINGTON			CLEVELAND		
EXEC. COST DEPT.			FORMULA		
SPEC. CARD			AMOUNT		
DATE			SLIP NO.		
FORM 159					