

CG 120 CODE BT-417-D PKG

NOV 3 1982

L2J09

PROCESSES APPROVED BY
() BT-417-D (L) BBK 11/20/81

(DATE) (LOT NUMBER)

EST. WT. ^{2,147} 2,147 LBS.TYPED BY: JMH
STANDARD HRS. TIME M

PREPARATION NOTES:

Pumped press

EQUIP MENT	NAME: MONASTRAL BLUE GF	1 PAGE	USE LBS	N-CODE	ACCT LBS
SV 1	1 RUN 2-3" (+/-200G) WATER INTO V-				
	2 USE STATION # , PRESET WATER METER PER CHART FOR WATER ADDITION TO FULL TOTES, THEN USING MODE 4, PUMP IN 5 FULL TOTES (+/-2600# 100%)			8710-A	
	GALS OF WATER				
	LOT	Net Pkts	16	±100%	%
	M287-B	24.9	488.0		
	M278-B	24.8	453.8		
	577-A	22.9	532.2		
	516-A	13.0	237.5		
	490-A	22.0	441.1		
		77.6	TOTAL	±100%	
	3 WEIGH & ADD		ASSUME 30%	10	7.8
	4 STIR 5 MIN				
	5 RECORD: PH	7.0-8.0			
	6 IF NECESSARY ADJ TO PH 7.0-8.0	ASSUME 50%			
	7 & RECORD PH	M			
	8 HEAT TO 120-125 DEG F IN 30-35 MIN				
	RECORD: TEMP	DEG F			
	STOP ACTIVATOR, RECORD VOL				

MISC 9 CALC EST WGT:
2 2218 ±100% X 0.968 = 2,147 ± EST. WT.
10 RECORD EST. WT. ON MAKE & PROCESS CARDS

START	FIN	OPTR

Pumped 5 Totes 10/28 B.L
Batch Completed

NOV 1 1982

N-8710-A

LOT #

TARE WT. 325

490-A

NET WT.

1419

% SOLIDS

27.0

NET SOLIDS

491.1

78E 241

TOTE BINS IN LOT

A

PACKED BY

N-8710-A

LOT #

TARE WT. 327

5/6A

NET WT. 1750

% SOLIDS 13.0

NET SOLIDS 227.5

TOTE 729 ✓

TOTE BINS IN LOT 7

PACKED BY

N-8710-A

LOT #

TARE WT. 330

577-A

NET WT.

1999

% SOLIDS

27.9

NET SOLIDS

557.7

Tote 532 ✓

TOTE BINS IN LOT

A

PACKED BY

N-8710-A

LOT #

TARE WT

NET WT

% SOLIDS

NET SOLIDS

TOTE BINS IN LOT

PACKED BY

N-3710-A

TARE WT

LOT

NET WT

% SOLIDS

NET SOLIDS

TOTE BINS IN LOT

PACKED BY