CG 18 CODE GT-751-D PKG.

→ MAR [illegible] 415

EST. WGT. LBS.

NOTE: MAKING — FILL IN EST WGT FROM BATCH CARD

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES		APPROVED BY
GT-751-D	(P)	AJC 05-09-77
GT-829-D	(A)	DCG 05-18-77
TYPED BY		
emw070279		

MAKING NOTES

REMARKS

NAME: MONASTRAL® GREEN G — NON-BLEEDING

INSTRUCTIONS — PRESSING — RECORD

VAT	264				
DATE	5-19-81				
TIME	8:30P				
RELEASED BY	S.B.				
PRESS	15 & 16	17 & 18	9 & 10	21	2
NO. OF CAKES	2 x 84	2 x 84	2 x 119	2 x 42	NYO

PRESS with AGITATION

WASH TO _____ OHMS

TEST AFTER _____ HOURS

LOAD on 4 cars

- DO NOT LOAD ON A-148-D CARS
- DO NOT USE A-148-D EQUIPMENT
- IF BLUE CARS USED, HIGH PRESSURE HOSE PANS BEFORE USE

SAMPLES

DELIVER TO

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	9 30 AM				
CAKES USED	42				
HRS TO FILL					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY BH

-DRYING-

Dry 14 hours at 220°F

LUMP: - OK - WET - SALTS - CONTAMINAT

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 15.

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT 2391

SAMPLED BY RELEASED BY RH

-GRINDING-

MILL 7 or 8 HSP 3/32" RP SCREEN 3560 RPM

MAX. TEMP. 200 °F

- IF A-148-D IN MILL LAST, SCRUB MILL, CLEAN DUST CABINET EQUIPMENT & CHANGE BAGS BEFORE GRINDING

SAMPLE WITHOUT MIXING

SAMPLES 1 Env 1 pt

DELIVER TO CTL

SCREEN	RPM
MAX. TEMP.	°F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY