MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE YC-16 LOT E1239

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	62	3,100		
STUMP	Lump -	3,064		

TOTAL NET WT. 3,100 PKG. N–CODE 1000

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	5/13/81	

CG 01 CODE YC-16-B PKG. 93
→ MAY -U·81- E1239

EST. WGT. 3130 LBS.

93
245

OK
FP

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	(A) YC-16-B	A.C 4-7-75
		JFH 5-5-75
		DCG 5-14-75
	TYPED BY	
	MAKING NOTES	

REMARKS

NAME: MOLYBDATE ORANGE — NON-BLEEDING

INSTRUCTIONS — -PRESSING- — RECORD

VAT	245				
DATE	5/11/81				
TIME	11:45 AM				
RELEASED BY	R.M.				
PRESS	91	98	(93)	2	25
NO. OF CAKES	42	32	32	32	32

PRESS
WASH TO 2000 — AGITATION — OHMS
TEST AFTER 2 — HOURS WITH 35-75 F WATER
LOAD ON 4 CARS

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	3:AM				
CAKES USED	32				
WATER ON	6 AM				
HRS. WASHED	6				
OHMS	4000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	4			1	

EXPLAIN LOSSES

SAMPLES
DELIVER TO — SAMPLED BY — RELEASED BY

-DRYING-

DRY 16 HOURS AT 220 F

LUMP: - OK - WET - SALTS - CONTAMINATED
DRYER SECTIONS USED:
No need for any Processing Losses Explain Please

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

SAMPLES
DELIVER TO — NO. CARS PULLED — SAMPLED BY — LUMP WGT. 3064 — RELEASED BY

-GRINDING-

MICROATOMIZE
SET ROOF GATE AT 5 INCHES AIR FLOW

MAGNEHELIC READING ON ATOMIZER PANEL 1.0"

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO C T L

DATE MIXED
SAMPLED BY — RELEASED BY

DUP050095700

1239
12
365

3.04 +
0.12 -
2.68 +
0.12 -
2.83 +
0.12 -
2.81 +
0.12 -
2.84 +
0.12 -
3.09 +
0.12 -
2.82 +
0.12 -
3.03 +
0.12 -
2.79 +
0.12 -
2.76 +
0.12 -
2.74 +
0.12 -
0.65 +
0.12 -
30.64 *

1325
124
41

3.46 +
0.14 -
3.39 +
0.14 -
3.40 +
0.14 -
3.27 +
0.14 -
3.33 +
0.14 -
3.49 +
0.14 -
3.52 +
0.14 -
3.79 +
0.14 -
14.18 +
40.71 *
40.71M+

8

DUP050095701