MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE RT695 LOT 36565

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	9	1229	13	
	STUMP Longwall	124/		

TOTAL NET WT. 1229 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	8/30/	292

0.T

140.+
145.+
147.+
135.+
125.+
133.+
121.+
142.+
141.+
1229.T

DUP050107411

36
1 80

AUG 19 1980

CG 36 CODE RT-695-D PKG. ____

→ NOV 20 80 36885

EST. WGT. 1350 LBS.

9 2h

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-695-D (M)	DCG 1-12
	IHD 2-25
TYPED BY	
LG 5-15-72	

~~Retyped 2-27-80~~ MnM

MAKING NOTES

REMARKS

NAME: BON RED DARK NON-BLEEDING

INSTRUCTIONS —PRESSING— RECORD

VAT	100				
DATE	8/20/80	NM			
TIME	5:15 AM				
RELEASED BY	T.L.				
PRESS	32	33	35	38	39
NO. OF CAKES	60	60	60	60	60

PRESS Without AGITATION

WASH TO 4000 OHMS with 35-75F water

TEST AFTER 16 HOURS

LOAD on 8 cars

A.K

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7 AM				
CAKES USED	32				
WATER ON	2:30 PM				
HRS. WASHED	16				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	ok				
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLES

DELIVER TO

SAMPLED BY RELEASED BY

—DRYING—

HOURS Dry 24 hours at L.V. H.V.

TEMP. 180 °F °F

SE 15-30

Mn Color

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO. CARS PULLED 7 DRUMS

LUMP WGT. 1241

SAMPLED BY RELEASED BY JAA

—GRINDING—

MILL 5 HSP 1/8" RP SCREEN 4600 RPM

MAX. TEMP. °F

Mn Color

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

SAMPLES Env & 2 pt cans

DELIVER TO C T L

DATE MIXED 4-22

SAMPLED BY RELEASED BY

DUP050107412

36885
51
348

1.89	+
0.14	-
1.86	+
0.14	-
1.95	+
0.14	-
1.88	+
0.14	-
1.92	+
0.14	-
1.91	+
0.14	-
1.98	+
0.14	-
12.41	*

DUP050107413