MD-3-A


PACKAGE TICKET (DRY AND PASTE ONLY)

CODE 67251 LOT E1415

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	23	2681	36	
	STUMP	Lumber	2685	

TOTAL NET WT. 2681 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	5-31	[illegible]



DUP050097237

CG 18 CODE GT-751-D PKG. ____

→ MAR [illegible] 15

EST. WGT. _____ LBS.

NOTE: MAKING — FILL IN EST WGT FROM BATCH CARD

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES		APPROVED BY
GT-751-D	(P)	AJC 05-09-77
GT-829-D	(A)	DCG 05-18-77
TYPED BY		
emw070279		

MAKING NOTES

REMARKS

NAME: MONASTRAL® GREEN G — NON-BLEEDING

INSTRUCTIONS						-PRESSING- RECORD					
VAT	2-V					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5-15-81					STARTED	8 pm				
TIME	12 3+2					CAKES USED	4/6				
RELEASED BY						HRS TO FILL					
PRESS	15 & 16	17 & 18	9 & 10	21	2						
NO. OF CAKES	2 x 84	2 x 84	2 x 119	2 x 42	MYD						
PRESS with AGITATION											
WASH TO _____ OHMS											
TEST AFTER _____ HOURS											
LOAD on 4 cars											
• DO NOT LOAD ON A-148-D CARS						CAKE CONDITION					
• DO NOT USE A-148-P EQUIPMENT						NO. CARS LOADED	6				
• IF BLUE CARS USED, HIGH PRESSURE HOSE PANS BEFORE USE						EXPLAIN LOSSES					
SAMPLES											
DELIVER TO						SAMPLED BY		RELEASED BY			

-DRYING-

Dry 14 hours at 220°F	LUMP: - OK - WET - SALTS - CONTAMINAT
	Color appears dry Cannot account for overweight bar heath
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS 15
SAMPLES	NO. CARS PULLED LUMP WGT. 2605
DELIVER TO	SAMPLED BY RELEASED BY RH

-GRINDING-

MILL 7 or 8 HSP 3/32" RP SCREEN 3560 RPM	SCREEN RPM
MAX. TEMP. 200 °F	MAX. TEMP. °F
• IF A-148-D IN MILL LAST, SCRUB MILL, CLEAN DUST CABINET EQUIPMENT & CHANGE BAGS BEFORE GRINDING	
	EXPLAIN LOSSES
SAMPLE WITHOUT MIXING	DATE MIXED
SAMPLES 1 Env + 1 pt	
DELIVER TO CTL	SAMPLED BY RELEASED BY

DUP050097238

2/
232

CG 18 CODE GT-751-D PKG. ____

→MAY -0·81-Ξ1418

EST. WGT. 2324 LBS.

NOTE: MAKING — FILL IN EST WGT FROM BATCH CARD

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	GT-751-D (P)	AJC 05-09-77
	GT-829-D (A)	DCG 05-18-77
	TYPED BY	
	emw070279	

MAKING NOTES

REMARKS

NAME: MONASTRAL® GREEN G NON-BLEEDING

INSTRUCTIONS — PRESSING — RECORD

VAT					
DATE					
TIME					
RELEASED BY					
PRESS	15 & 16	17 & 18	9 & 10	21	(2)
NO. OF CAKES	2 x 84	2 x 84	2 x 119	2 x 42	

PRESS with AGITATION

WASH TO _____ OHMS

TEST AFTER _____ HOURS

LOAD on 4 cars

SAMPLES

DELIVER TO

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED					
CAKES USED					
HRS TO FILL					
CAKE CONDITION					
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

Dry 14 hours at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT.

SAMPLED BY RELEASED BY

-GRINDING-

MILL 7 or 8 HSP 3/32" RP SCREEN 3560 RPM

MAX. TEMP. 200°F

SAMPLE WITHOUT MIXING

SAMPLES 1 Env

DELIVER TO C T L

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY

DUP050097239

1418
51
305

0.00 *

1.96 +
0.14
1.82 +
0.14
1.78 +
0.14
1.72 +
0.14
1.90 +
0.14
1.90 +
0.14
1.74 +
0.14
1.74 +
0.14
1.85 +
0.14
2.07 +
0.14
2.08 +
0.14
2.05 +
0.14
1.90 +
0.14
1.86 +
0.14
1.78 +
0.14
26.05 *

DUP050097240