A & L PRINTERS, NEWARK, N.J.

MD-2-A

ONLY 300 # PER DRUM

PACKAGE TICKET

(PRESSCAKE ONLY)

CODE YC-11-A LOT 38040

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
300	10	3000	33-P-4	
225	1	225	34	
		5	37	
		104		
		000		

TOTAL NET WT. 3225 D.C. _____ %

PKG. N-CODE _____

PROD. SPVR.	PROD. OPER.	DATE	WHSE. OPER.
BLC	365+452	11/26/80	

N35278

DUP050108358

#1 MEMBRANE

CG 46 CODE YC-11-A PKG. ____

→ NOV 25 80 38040

EST. WGT. 2238 LBS.

105 VAT 81"
Temp at Start 150 °F

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(D) YC-11-A	EWK 9-28-76
	BBK 10-17-77
	DCG 11-29-77
TYPED BY	
JTC 12-8-77	

MAKING NOTES

REMARKS

NAME: DALAMAR® YELLOW

BLEEDING

INSTRUCTIONS -PRESSING- RECORD

VAT				105	
DATE				11-25-80	
TIME				2.05 AM	
RELEASED BY				M.N.	
PRESS	32	33	35	M1	
NO. OF CAKES	60	62	60		

PRESS WITHOUT AGITATION

WASH TO 4000 OHMS WITH 35-75°F WATER

TEST AFTER 4 HOURS

LOAD IN METAL DRUMS AT 325# NET PER DRUM

AIR BLOW PRESSCAKE 15 MIN AT 40PSI

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7:30 pm				
CAKES USED	6 m				
WATER ON	8:45 pm				
HRS. WASHED	3				
OHMS	4200				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLES THIEF SAMPLE & FILL 1-8 oz. jar + 1 qt (R&D)

DELIVER TO CTL for color

SAMPLED BY RELEASED BY

-DRYING-

DRY — HOURS AT — °F

DO NOT DRY

LUMP: — OK — WET — SALTS — CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO. DRUMS

NO. CARS PULLED

LUMP WGT.

SAMPLED BY

RELEASED BY

-GRINDING-

MILL SCREEN RPM

MAX. TEMP. °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

SAMPLES

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050108359