ONE

GALLON



O'BRIEN'S

Flexico®

MARINE TYPE SUPER ENAMEL

CHOCOLATE

FOR
INSIDE
OUTSIDE
USE

MANUFACTURED IN U.S.A. BY THE O'BRIEN CORPORATION • SOUTH BEND, INDIANA

O'BRIEN'S FLEXICO ENAMEL

Made with Alki-therm, Flexico is a deluxe high-gloss enamel which imparts unusual beauty and extra protection to almost any surface. Popular for interior use in kitchens and bathrooms—on walls, trim, cabinets, furniture. Excellent for exterior work—on boats, porch furniture, etc. Its marine type formulation insures a tough, hard finish that's extremely resistant to water, sun, wear and abrasion. Easily applied with brush or spray. Flows on—no brush marks. Dries quickly.

DIRECTIONS FOR USE

NEW WOOD — apply one coat of O'Brien's White Surfacer or Double-Up Undercoat and finish with one or two coats of Flexico. Note—on boats use three thin coats of Flexico only. Thin first coat 10% with turpentine.

NEW PLASTER — apply one coat of O'Brien's Liquid Velvet Wall Primer and Sealer. Finish with one or two coats of Flexico.

NEW METAL—one coat of O'Brien's White Surfacer or Double-Up Undercoat followed with one or two coats of Flexico. Note—Use Tame-Rust Metal Primer on new steel boats. Galvanized or fiber glass boats require special primers and treatment.

OLD PAINTED SURFACES IN GOOD CONDITION —one or two coats of Flexico.

REGISTERED
REGN. No. 2513
DATE 1-22-43

GENERAL DIRECTIONS — mix the enamel thoroughly before using and apply with a soft bristle brush. Sand and dust carefully between coats.

SURFACE PREPARATION — surfaces should be clean and dry, free of wax, oil, grease or soap compounds.

THINNING — Flexico is ready for use. If it appears too heavy and easier brushing is desired, thin accordingly with turpentine

DRYING—allow overnight drying between coats.

TINTING — Flexico Colors may be tinted with O'Brien's Tone-All Colors.

SAFE FOR BABY FURNITURE
LEAD FREE
DO NOT TAKE INTERNALLY

CAUTION! COMBUSTIBLE
Keep away from heat and open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use. Use with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN.

FLEXICO CHOCOLATE

Pigment		15.28%
C.P. Brown Iron Oxide	53.28%	
C.P. Yellow Iron Oxide (Hydrated)	44.65%	
Carbon Black	1.77%	
	100.00%	
Vehicle		84.72%
Modified Soya Alkyd Resin	41.94%	
Aromatic Hydrocarbon	4.73%	
Mineral Spirits & Driers	53.33%	
	100.00%	

THE O'BRIEN CORPORATION

SOUTH BEND, IND. BALTIMORE, MD.
OKLA. CITY, OKLA. SAN FRANCISCO, CAL.
LOS ANGELES, CAL.

49 TOC 001660