Name S.W.P. Westchester Gray Card No. 1 Replaces No.

POUNDS	GALLONS	MATERIAL No.
325		20 L
100		2174
380		412
113		BW 102-over
?		BB 10
?		BO 31
?		BO 30
	5/8	(12)W
	27 1/4	(2)
	19	(48)
	1	(543)
	3	(5250)
	19	(348)
	4	(141)

Customer S.W.CO.

To Match New Color See Ry477

Reason for Revision NEW VOID

Per V. Mills letter dated 7-30-45 Subj. Re-Alignment of Trade Sales Ex Numbers

DATE BY

Viscosity 25-30" @75° #3t Sty hrs. after grind

Viscosity at hrs. after grind

% Solids (Run)

Wt./Gal T 14.37

Baume

Std. of Fineness 3H

Normal Output 100

Est. Mfg. Loss 2%

Department B

Package

Parallel No.'s

Royalty: Yes □; No □; X □; W □

Label Analysis Checked-Date

Label: No Red □ X Red □

New Std. Sample Required yes

Date Rec'd

Mill Roller Bleed?

Lbs. or Gals. per hour

Approved

Formulator Wm J Radin

Supt.

N16240

MANUFACTURING INSTRUCTIONS:

PRODUCTION		
DATE	SLIP No.	AMOUNT

Reduction: Amount _____ **Reducer Used** _____

Application: Surface Wood **Method** Brush

No. Coats _____ **Undercoater Used** _____

Drying Time: Touch 18 hrs **Handle** _____ **Recoat** 48 hrs

Rub _____ **Sand** _____ **Wrap** _____ **Stencil** _____

Baking Time and Temp. _____

Gloss Oil **Film** Tough

Special Tests _____

FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE	FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
CLEVELAND				ALLIED RESEARCH			
NEWARK				GIBBSBORO			
KENSINGTON				DAYTON			
OAKLAND				DETROIT			
DALLAS				LONDON			
LOS ANGELES				AUSTRALIA			
MONTREAL				M-S			
COST DEPT.				CHI. TECH. SERV.			

0007-SWP-061462