ONE

GALLON

O'BRIEN'S

"75"

HOUSE PAINT

FOR ANY EXTERIOR SURFACE

NILE GREEN

MADE IN U.S.A. BY THE O'BRIEN CORPORATION • SOUTH BEND, INDIANA • BALTIMORE, MARYLAND

O'BRIEN'S "75" HOUSE PAINT

O'Brien's new "75" House Paint represents the very finest in a top quality exterior paint. Made with patented *Pre-Shrunk Thermolyzed Oils,* it looks better longer on any type of exterior surface — wood siding and trim, shingles, brick, concrete, metal.

The extra hiding of the new "75" House Paint White insures the *whitest* possible jobs in only one coat. Actually *gets whiter* the longer it's on. Smooth easy brushing, more coverage per gallon and greater durability and beauty make "75" the best house paint "buy" on the market. No other outside paint can match it for performance and lasting beauty.

"75" HOUSE PAINT PRIMING WHITE

This is a specially formulated undercoat for use on exterior surfaces under "75" House Paint and other similar products. It controls the penetration of the oils in the paint applied over it, and dries dull permitting fast application of the finish coat. Easy to apply, its tremendous hiding provides a perfect base for final coat.

"75" TINTING WHITE

This product has all the application and performance features of regular "75" House Paint except that **it is to be used for tinting purposes only.** Can be easily tinted with Pure Liquid Oil Colors or by intermixing with other standard redi-mixed "75" House Paint colors. Never use straight out of the bucket as a White color.

CAUTION! COMBUSTIBLE
Keep Away from
Heat and Open Flame
CONTAINS LEAD OR OTHER COMPOUNDS HARMFUL IF EATEN
Do not apply on toys, furniture or interior surfaces which might be chewed by children. Use with adequate ventilation. Avoid breathing vapor or spray mist. Avoid prolonged contact with skin. Wash thoroughly after handling and before eating or smoking. Keep container closed when not in use



75 HOUSE PAINT — White for Tinting

Pigment	55.61%
Titanium Dioxide	9.27%
Titanium Calcium Pigment	22.22%
35% Leaded Zinc Oxide	44.50%
Barium Sulphate	5.96%
Magnesium Silicate	18.02%
	100.00%
Vehicle	44.39%
Thermolized Tung Oil	10.59%
Raw Linseed Oil	36.85%
Refined Soya Bean Oil	10.17%
Heat Treated Linseed Oil	12.70%
Mineral Spirits & Driers	30.40%
	100.00%

REG'N. No. 2513
DATE 6-18-52

DIRECTIONS FOR USE

FOR NEW UNPAINTED SURFACES

1st Coat—O'Brien's "75" House Paint Priming White. Tint to approximate shade of finish coat.*

2nd Coat—O'Brien's "75" House Paint.

FOR OLD PAINTED SURFACES

One Coat Work — one coat of "75" House Paint will give a satisfactory result providing the surfaces are reasonably clean — in good condition and there is to be no radical change of color.

Two Coat Work — over badly weathered or extremely dirty surfaces, follow two coat system listed above under "New Unpainted Surfaces".

*For light colors tint Priming White with O'Brien's Oil Colors. For dark colors mix one-half Priming White and one-half "75" House Paint of the finish color.

GENERAL RECOMMENDATIONS

WEATHER — Outside painting should never be done when the weather is damp or the temperature below 60° F.

SURFACES — Surfaces to be painted should be perfectly dry and free of grease, oil, dust and loose dirt.

SPRAYING — "75" House Paint may be sprayed by an experienced operator.

DRYING — Allow at least 48 hours good drying weather between coats. When temperature is low, allow at least 96 hours drying.

Stir Paint Well Before and During Use. When Necessary — Thin with Turpentine or O'Brien's Reducit.

THE O'BRIEN CORPORATION

SOUTH BEND, IND. **BALTIMORE, MD.**
OKLA. CITY, OKLA. **SAN FRANCISCO, CAL.**

49 TOC 001127