

C

O

P

Y

Not Indented

CC: J. A. Klossmann, Lab.
J. H. Lowell, Lab.
W. P. Scilio, Phila. Plant

File: 6585

Marshall Laboratory
March 21, 1957

R. H. BELL, MGR.
PARLIN

ATTENTION: C. B. SHERIDAN

USE OF RL-3113 in "LUCITE" ACRYLIC LACQUER

On Page 5 of your February, 1957, Parlin Plant Laboratory Monthly Report, you stated that tests were being run to determine the amount of H-654 butyl benzyl phthalate that could be replaced by RL-3113. The Research Division is opposed to the use of RL-3113 in any quantities because it is thinned with H-596. We know from extensive durability studies that H-596 has a detrimental effect on "Lucite" durability.

If RL-3113 could be thinned with H-583, there would be no objection whatsoever from the Research Division, since H-583 is used extensively in our present formulations and has no adverse effect on durability.

G. I. MULHOLLAND

GIM:etk
3-21

cc:eod