CG.01 . CODE YE-698-D PKG ____

LOT **L2H26**

EST. WT. 5527* LBS.

012/18

YE-698-D (T) FWP 10/18/82
ALTERNATE

COMTYP JOB NAME: 01YE698DPT

MAKING NOTES: _____

= PRESSING =

INSTRUCTIONS					RECORD					
VAT	247				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	11-4				STARTED					
TIME	3:00A				CAKES USED					
RELEASED BY	RWB				WATER ON					
PRESS	2	92	93		HRS. WASHED					
NO.OF CAKES	54	54	54		M MHOS					
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER					M MHOS					
TEST AFTER 2 HOURS					HRS. WASHED					
LOAD ON 7 CARS					M MHOS					
					CAKE CONDITION					
					NO CARS LOADED					
					EXPLAIN LOSSES					

SAMPLES 8 OZ
DELIVER TO CTL.

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

DELIVER

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT

CO-GRIND PER CTL INSTRUCTIONS

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "5" FOR HIGH AIR FLOW

GRINDING

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE W/O MIXING
SAMPLES 1 ENV & 1 PINT CAN IF GROUND SEPARATELY
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY