MD-3-A

PACKAGE TICKET

CODE Y7820 LOT G2547

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
		20	2720	40
	STUMP			

TOTAL NET WT. 2720

LUMP WT. 2737 PKG. N-CODE

PROD. SUPV. DATE 8/3 OPERATOR

N32601

PRODUCT NAME = DALAMAR YELLOW - R

CG 46 CODE YT-820-D PKG ____

LOT G2J47 JUL 22 1982

EST. WT. 2563* LBS. (20) 35/106

BLEEDING 1/12/82

PROCESSES APPROVED BY
YT-820-D (D) EWK 10/21/81

TYPED BY: JMH

MAKING NOTES _____

JOB NAME: 46YT820DPD

= PRESSING =

106 INSTRUCTIONS

VAT
DATE 7-23-82
TIME 73.0
RELEASED 80

PRESS	NO.OF CAKES
32	60
33	62
(35)	60
M-1	64

PRESS WITHOUT AGITATION
WASH TO 250 M MHOS - 35-75 F WATER
TEST AFTER 4 HOURS
LOAD ON 10 CARS FOR 30 SERIES PRESS
LOAD ON 6 CARS FOR M-1 PRESS
MEMBRANE PRESS - SLURRY TEMP MUST NOT EXCEED 160*F OR 15 PSI BACK PRESSURE AT THE INLET FEED GAUGE.
WATER TEST, FILL, WASH & COMPRESS PER O.P.# P.0081
SAMPLES
DELIVER TO

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1130am				
CAKES USED	60				
WATER ON	6am				
HRS. WASHED	8				
M MHOS	950				
HRS. WASHED					
M MHOS					
HRS. WASHED					
M MHOS					
CAKE CONDITION					
NO CARS LOADED	8				

EXPLAIN LOSSES 8

SAMPLED BY
RELEASED BY SH

= DRYING =

DRY 30 HOURS AT 180 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1QT
DELIVER TO

NO CARS PULLED 8
SAMPLED BY
RELEASED BY

NO DRUMS 20
LUMP WGT 2737 #

BH

= GRINDING =

MILL 10 LSP 1/8" RP SCREEN 1750 RPM
MAX. TEMP. 140* F
INERT MILL WITH CO2 WHEN GRINDING PER O.P.# O.F. 0043

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 2 ENV & 2 PT CANS
DELIVER TO CTL

DATE MIXED 8-2-82

SAMPLED BY 389
RELEASED BY

N32601.01

DUP050463735

47
51
231

0.00 *

1.46 +
0.14 -
1.47 +
0.14 -
1.50 +
0.14 -
1.56 +
0.14 -
1.45 +
0.14 -
1.46 +
0.14 -
1.48 +
0.14 -
1.50 +
0.14 -
1.50 +
0.14 -
1.49 +
0.14 -
1.50 +
0.14 -
1.46 +
0.14 -
1.49 *
0.14 -
1.50 +
0.14 -
1.60 +
0.14 -
1.58 +
0.14 -
1.63 +
0.14 -
1.50 +
0.14 -
1.50 +
0.14 -
1.54 +
0.14 -
27.37 *

N32601.02

DUP050463736